

# LNPT<sup>™</sup> FARADEx<sup>™</sup> COMPOUND MS003

MS-1003

## DESCRIPTION

LNP FARADEx MS003 compound is based on Polypropylene (PP) resin containing 15% stainless steel fiber. Added features of this grade include: Electrically Conductive, EMI/RFI shielding.

GENERAL INFORMATION	
Features	Electrically Conductive, EMI/RFI Shielding, No PFAS intentionally added
Fillers	Stainless Steel Fiber
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components
Industrial	Electrical, Material Handling
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	19	MPa	ASTM D638
Tensile Stress, break	15	MPa	ASTM D638
Tensile Strain, yield	6.2	%	ASTM D638
Tensile Strain, break	88.4	%	ASTM D638
Tensile Modulus, 50 mm/min	1190	MPa	ASTM D638
Flexural Stress	27	MPa	ASTM D790
Flexural Modulus	1190	MPa	ASTM D790
Tensile Stress, yield	21	MPa	ISO 527
Tensile Stress, break	15	MPa	ISO 527
Tensile Strain, yield	5.2	%	ISO 527
Tensile Strain, break	72	%	ISO 527
Tensile Modulus, 1 mm/min	1300	MPa	ISO 527
Flexural Stress	32	MPa	ISO 178
Flexural Modulus	1500	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	1226	J/m	ASTM D4812
Izod Impact, notched, 23°C	267	J/m	ASTM D256
Multiaxial Impact	22	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	80	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	25	kJ/m <sup>2</sup>	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	92	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	53	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.04E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.72E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.43E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.7E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	56	°C	ISO 75/Af
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.01	g/cm <sup>3</sup>	ASTM D792
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	1.2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.3	%	ASTM D955
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	1.2	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.3	%	ISO 294
Density	1.01	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/24hrs)	0.03	%	ISO 62-1
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity <sup>(3)</sup>	1.E+04	Ω.cm	ASTM D257
Surface Resistivity <sup>(3)</sup>	1.E+03	Ω	ASTM D257
Static Decay, 5000V to <50V	<0.01	Seconds	FTMS101B
Shielding Effectiveness @ 3mm	50 – 65	dB	SABIC method
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	230 – 250	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Mold Temperature	30 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	25 – 50	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.