

LNPT[™] ELCREST[™] EXL9334P

DESCRIPTION

LNP ELCRES EXL9334P is based on Polycarbonate (PC) copolymer resin with excellent low temperature ductility, robust flame retardancy, UV stabilized with F1 rating and good processability. It has good electrical tracking resistance with UL CTI PLC=0 and IEC CTI=600V intended for high voltage applications such as photovoltaic connectors.

GENERAL INFORMATION	
Features	Flame Retardant, Dimensional stability, Low temperature impact, Weatherable /UV stable, Tracking resistance
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Hydrocarbon and Energy	Energy Storage

TYPICAL PROPERTY VALUES

Revision 20241024

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	57	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	90	%	ASTM D638
Tensile Modulus, 5 mm/min	2050	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	87	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2110	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	53	MPa	ISO 527
Tensile Stress, break, 5 mm/min	54	MPa	ISO 527
Tensile Strain, break, 5 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Strength, 2 mm/min	81	MPa	ISO 178
Flexural Modulus, 2 mm/min	2080	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact			
notched, 23°C	750	J/m	ASTM D256
notched, -30°C	650	J/m	ASTM D256
notched, -35°C	550	J/m	ASTM D256
notched, -40°C	420	J/m	ASTM D256
unnotched, 23°C	NB	J/m	ASTM D4812
unnotched, -30°C	NB	J/m	ASTM D4812
notched 80*10*3 +23°C	61	kJ/m ²	ISO 180/1A
notched 80*10*3 -30°C	59	kJ/m ²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Instrumented Dart Impact Energy @ peak, 23°C	64	J	ASTM D3763
Instrumented Dart Impact Total Energy, 23°C	65	J	ASTM D3763
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	122	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	136	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	123	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	138	°C	ISO 75/Bf
CTE, 23°C to 80°C, flow	7.9E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, xflow	8.3E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	6.5E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.1E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	7.9E-5	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.3E-5	1/°C	ISO 11359-2
CTE, -40°C to 40°C, flow	6.6E-5	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7E-5	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	142	°C	ISO 306
Vicat Softening Temp, Rate B/120	143	°C	ISO 306
Relative Temp Index, Elec ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	115	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	130	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.22	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ISO 62-1
Melt Flow Rate, 300°C/1.2 kgf	8	g/10 min	ASTM D1238
Melt Flow Rate, 300°C/2.16 kgf	16	g/10 min	ASTM D1238
Melt Flow Rate, 300°C/5.0 kgf	41	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/1.2 kg	7	cm ³ /10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/2.16 kg	14	cm ³ /10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/5.0 kg	37	cm ³ /10 min	ASTM D1238
Mold Shrinkage, flow ⁽³⁾	0.8	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.8	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity	8.6E15	Ω	ASTM D257
Volume Resistivity	1.8E15	Ω.cm	ASTM D257
Dielectric Constant, 1.1 GHz	2.87	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0105	-	SABIC method
Dielectric Constant, 1.9 GHz	2.88	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0097	-	SABIC method
Dielectric Constant, 5 GHz	2.87	-	SABIC method
Dissipation Factor, 5 GHz	0.0079	-	SABIC method
Dielectric Constant, 10 GHz	2.87	-	SABIC method
Dissipation Factor, 10 GHz	0.0074	-	SABIC method
Comparative Tracking Index (UL) {PLC} ⁽²⁾	0	PLC Code	UL 746A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-104582145	-	-
UL Recognized, 94-5VA Flame Class Rating	≥3.0	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	≥2.5	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥1.2	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 290	°C	
Nozzle Temperature	250 – 285	°C	
Front - Zone 3 Temperature	260 – 290	°C	
Middle - Zone 2 Temperature	255 – 285	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	70 – 120	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.