

# ULTEM™ RESIN 9075

REGION ASIA

## DESCRIPTION

High flow Polyetherimide blend. Meets FAR 25.853 and OSU 65/65 with low toxicity, smoke, and flame evolution. ECO Conforming.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

INDUSTRY	SUB INDUSTRY
Automotive	Aerospace
Mass Transportation	Rail

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	96	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	85	%	ASTM D638
Tensile Modulus, 5 mm/min	3300	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	144	MPa	ASTM D790
Flexural Stress, brk, 2.6 mm/min, 100 mm span	141	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	3240	MPa	ASTM D790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	69	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	2082	J/m	ASTM D256
Gardner, 23°C	35	J	ASTM D3029
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	188	°C	ASTM D648
<b>PHYSICAL</b>			
Specific Gravity	1.3	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	2.4	g/10 min	ASTM D1238
Halogen Content	0	%	SABIC method
<b>FLAME CHARACTERISTICS</b>			
FAA Flammability, FAR 25.853 A/B	SECT A-1	-	FAR 25.853
OSU total heat release (2 minute test)	10	kW-min/m²	FAR 25.853
Vertical Burn a (60s) passes at	1	Seconds	FAR 25.853
Vertical Burn b (12s) passes at	0	Seconds	FAR 25.853
<b>INJECTION MOLDING</b>			
Drying Temperature	135 – 145	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	10	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 370	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	350 – 370	°C	
Front - Zone 3 Temperature	350 – 370	°C	
Middle - Zone 2 Temperature	345 – 365	°C	
Rear - Zone 1 Temperature	340 – 360	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	
PROFILE EXTRUSION			
Drying Temperature	130 – 140	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 330	°C	
Barrel - Zone 1 Temperature	280 – 300	°C	
Barrel - Zone 2 Temperature	295 – 320	°C	
Barrel - Zone 3 Temperature	305 – 330	°C	
Barrel - Zone 4 Temperature	310 – 335	°C	
Hopper Temperature	80 – 100	°C	
Adapter Temperature	285 – 335	°C	
Die Temperature	275 – 330	°C	
Calibrator Temperature	140 – 170	°C	
Calibrator 2 Temperature	90 – 130	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.