

NORYL GTX™ RESIN GTX820

REGION EUROPE

DESCRIPTION

NORYL GTX820 resin is a 20% glass fiber reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade has high stiffness (flexural modulus 4000 MPa), excellent chemical resistance, and high heat resistance. NORYL GTX820 resin is an excellent candidate for a wide variety of applications including valves for water management.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Building and Construction	Water Management
Electrical and Electronics	Electronic Components
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20241015

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	100	MPa	ISO 527
Tensile Stress, break, 5 mm/min	95	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.5	%	ISO 527
Tensile Strain, break, 5 mm/min	3.5	%	ISO 527
Tensile Modulus, 1 mm/min	5700	MPa	ISO 527
Flexural Stress, break, 2 mm/min	145	MPa	ISO 178
Flexural Modulus, 2 mm/min	5200	MPa	ISO 178
Ball Indentation Hardness, H358/30	100	MPa	ISO 2039-1
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	40	kJ/m ²	ISO 180/1U
Charpy Impact, notched, 23°C	7	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -20°C	5	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	50	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/120	220	°C	ISO 306
Thermal Conductivity	0.25	W/m·°C	ISO 8302

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
CTE, 23°C to 60°C, flow	2.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.8E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec ⁽²⁾	120	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	60	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	125	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.25	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.08	%	ISO 62
Water Absorption, (23°C/saturated)	3.2	%	ISO 62-1
Melt Volume Rate, MVR at 280°C/5.0 kg	6	cm ³ /10 min	ISO 1133
Mold Shrinkage on Tensile Bar, flow ⁽³⁾	0.3 – 0.7	%	SABIC method
ELECTRICAL ^{(1) (2)}			
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	1.5	mm	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-236570	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
Oxygen Index (LOI)	26	%	ISO 4589
INJECTION MOLDING ⁽³⁾			
Drying Temperature	100 – 110	°C	
Drying Time	2 – 3	Hrs	
Maximum Moisture Content	0.07	%	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	270 – 290	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 100	°C	
Hopper Temperature	60 – 80	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.