

LNPT[™] STAT-KON[™] COMPOUND DE0069F

DC-1006 FR SM

REGION AMERICAS

DESCRIPTION

LNP STAT-KON DE0069F compound is based on Polycarbonate (PC) resin containing 30% carbon fiber. Added features of this grade include: Electrically Conductive, Flame Retardant, Superior Molding.

GENERAL INFORMATION	
Features	Flame Retardant, Electrically Conductive, High Flow, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20230713

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	146	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	146	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	1.6	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.6	%	ASTM D638
Tensile Modulus, 5 mm/min	17320	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	210	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	212	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	14640	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	137	MPa	ISO 527
Tensile Stress, break, 5 mm/min	137	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.2	%	ISO 527
Tensile Strain, break, 5 mm/min	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	16670	MPa	ISO 527
Flexural Modulus, 2 mm/min	14560	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	464	J/m	ASTM D4812
Izod Impact, notched, 23°C	52	J/m	ASTM D256
Multiaxial Impact	2	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	10	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	24	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	5	kJ/m ²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	146	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	142	°C	ASTM D648
CTE, -30°C to 30°C, flow	7.E-06	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	7.E-06	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	148	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	143	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.36	-	ASTM D792
Density	1.36	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.07	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.1 – 0.3	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.1 – 0.4	%	ASTM D955
Density	1.36	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.13	%	ISO 62
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽⁴⁾	11.E+01 – 1.E+06	Ω	ASTM D257
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101343401	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Measurement meets requirements as specified in ASTM D4496.

(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.