

# LNPT<sup>™</sup> FARADEx<sup>™</sup> COMPOUND NS003

PCA-S-1003

## DESCRIPTION

LNP FARADEx NS003 compound is based on Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend containing 15% stainless steel fiber. Added features of this grade include: Electrically Conductive, EMI/RFI shielding.

GENERAL INFORMATION	
Features	Electrically Conductive, EMI/RFI Shielding, No PFAS intentionally added
Fillers	Stainless Steel Fiber
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components
Industrial	Electrical, Material Handling
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	50	MPa	ISO 527
Tensile Stress, break	46	MPa	ISO 527
Tensile Strain, yield	3.5	%	ISO 527
Tensile Strain, break	6	%	ISO 527
Tensile Modulus, 1 mm/min	2700	MPa	ISO 527
Flexural Stress	86	MPa	ISO 178
Flexural Modulus	2800	MPa	ISO 178
Tensile Stress, yield	52	MPa	ASTM D638
Tensile Stress, break	49	MPa	ASTM D638
Tensile Strain, yield	3.3	%	ASTM D638
Tensile Strain, break	4.7	%	ASTM D638
Tensile Modulus, 50 mm/min	3100	MPa	ASTM D638
Flexural Stress	89	MPa	ASTM D790
Flexural Modulus	2990	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched 80°10*4 +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80°10*4 +23°C	32	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched, 23°C	74	J/m	ASTM D256
Izod Impact, unnotched, 23°C	573	J/m	ASTM D4812
Instrumented Dart Impact Energy @ peak, 23°C	15	J	ASTM D3763

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>THERMAL <sup>(1)</sup></b>			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Bf
CTE, -40°C to 40°C, flow	5.90E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.20E-05	1/°C	ISO 11359-2
HDT, 0.45 MPa, 3.2 mm, unannealed	120	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.30E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.74E-05	1/°C	ASTM E831
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.21	g/cm <sup>3</sup>	ISO 1183
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.35	%	ISO 294
Density	1.24	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.3	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.35	%	ASTM D955
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity <sup>(3)</sup>	1.E+04	Ω.cm	ASTM D257
Surface Resistivity <sup>(3)</sup>	1.E+01 – 1.E+03	Ω	ASTM D257
Static Decay, 5000V to <50V	<0.01	Seconds	FTMS101B
Shielding Effectiveness @ 3mm	50 – 65	dB	SABIC method
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	220 – 260	°C	
Front - Zone 3 Temperature	245 – 255	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	220 – 230	°C	
Mold Temperature	40 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.