

# LNPTM LUBRICOMPTM COMPOUND ECL36

ECL-4036

REGION EUROPE

## DESCRIPTION

LNP LUBRICOMP ECL36 compound is based on Polyetherimide (PEI) resin containing 30% carbon fiber, 15% PTFE. Added features of this grade include: Wear Resistant, Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength, High temperature resistance
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break, 5 mm/min	160	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	21600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	256	MPa	ISO 178
Flexural Strain, break, 2 mm/min	1.6	%	ISO 178
Flexural Modulus, 2 mm/min	18500	MPa	ISO 178
Flexural Strain, break, 2 mm/min, 80°C	1.5	%	ISO 178
Flexural Strain, break, 2 mm/min, 120°C	1.4	%	ISO 178
Flexural Strain, break, 2 mm/min, 150°C	1.6	%	ISO 178
Flexural Strain, break, 2 mm/min, 200°C	1	%	ISO 178
Flexural Stress, yield, 2 mm/min, 80°C	214	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 120°C	182	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 150°C	145	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 200°C	91	MPa	ISO 178
Flexural Modulus, 2 mm/min, 80°C	17900	MPa	ISO 178
Flexural Modulus, 2 mm/min, 120°C	17400	MPa	ISO 178
Flexural Modulus, 2 mm/min, 150°C	16400	MPa	ISO 178
Flexural Modulus, 2 mm/min, 200°C	15300	MPa	ISO 178

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched 80*10*3 -40°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	18	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -40°C	25	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
Specific Heat	1890	J/kg-K	ASTM E1269
CTE, 23°C to 60°C, flow	9.E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	2.8E-05	1/°C	ISO 11359-2
Thermal Conductivity	0.33	W/m-K	ASTM D5930
<b>PHYSICAL <sup>(1)</sup></b>			
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.25	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.1 – 0.4	%	ISO 294
Wear Factor Washer	31	10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.39	-	ASTM D3702 Modified: Manual
Static COF	0.48	-	ASTM D3702 Modified: Manual
Density	1.49	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/24hrs)	0.32	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.21	%	ISO 62
Melt Volume Rate, MVR at 345°C/10.0 kg	4 – 6	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity	1.E+01 – 1.E+06	Ω	ASTM D257
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 375	°C	
Rear - Zone 1 Temperature	355 – 365	°C	
Middle - Zone 2 Temperature	360 – 370	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Nozzle Temperature	365 – 375	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.