

LNPT[™] STAT-KON[™] COMPOUND AE002

AC-1002

REGION AMERICAS

DESCRIPTION

LNP STAT-KON AE002 compound is based on Acrylonitrile Butadiene Styrene (ABS) resin containing 10% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20240626

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	86	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	83	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	1.5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.5	%	ASTM D638
Tensile Modulus, 50 mm/min	7400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	114	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	6660	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	82	MPa	ISO 527
Tensile Stress, break, 5 mm/min	82	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.4	%	ISO 527
Tensile Strain, break, 5 mm/min	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	7400	MPa	ISO 527
Flexural Stress	112	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	237	J/m	ASTM D4812
Izod Impact, notched, 23°C	51	J/m	ASTM D256
Multiaxial Impact	2	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	9	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	106	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	101	°C	ASTM D648
CTE, -30°C to 30°C, flow	3.31E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	8.25E-05	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	101	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.16	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.23	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.2 – 0.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	0.3 – 0.5	%	ASTM D955
Density	1.16	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.35	%	ISO 62
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽³⁾	1.E+01 – 1.E+05	Ω	ASTM D257
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.05 – 0.1	%	
Melt Temperature	260	°C	
Front - Zone 3 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.