

# LNPTM LUBRICOMPTM COMPOUND IZL33

## DESCRIPTION

LNPTM LUBRICOMP IZL33 compound is based on Nylon 6/12 resin containing 15% milled glass and 15% PTFE. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Low Warpage, Wear resistant, Dimensional stability
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 612 (Nylon 612)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Flexural modulus	2500	MPa	ASTM D790
Flexural Modulus	2707	MPa	ISO 178
Flexural Stress	73	MPa	ASTM D790
Tensile Modulus, 5 mm/min	3410	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4.6	%	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.3	%	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	44	MPa	ASTM D638
Tensile Modulus, 1 mm/min	3338	MPa	ISO 527
Tensile Stress, yield, 5 mm/min	45	MPa	ISO 527
Tensile Stress, break, 5 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	7	%	ISO 527
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Izod Impact, unnotched, 23°C	188	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	13	kJ/m <sup>2</sup>	ISO 180/1U
Multiaxial Impact	1.22	J	ISO 6603
Multiaxial Impact	3.6	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.8 MPa, 3.2mm, unannealed	128	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	190	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	89	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	175	°C	ISO 75/Bf
CTE, -30°C to 30°C, flow	0.000076	1/°C	ASTM E831
CTE, -30°C to 30°C, xflow	0.000088	1/°C	ASTM E831
<b>PHYSICAL <sup>(1)</sup></b>			
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	1.9	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	1.7	%	ASTM D955
Moisture Absorption, (23°C/50% RH/24 hrs)	0.15	%	ASTM D570
Moisture Absorption (23°C / 50% RH)	0.11	%	ISO 62
Wear Factor Washer	77	10 <sup>-10</sup> in <sup>4</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.36	-	ASTM D3702 Modified: Manual
Static COF	0.41	-	ASTM D3702 Modified: Manual
Wear Factor Ring	16.7	10 <sup>-10</sup> in <sup>4</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Specific Gravity	1.3	-	ASTM D792
Density	1.29	g/cm <sup>3</sup>	ASTM D792
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	82	°C	
Drying Time	4	Hrs	
Melt Temperature	271 – 276	°C	
Front - Zone 3 Temperature	271 – 282	°C	
Middle - Zone 2 Temperature	260 – 271	°C	
Rear - Zone 1 Temperature	254 – 265	°C	
Mold Temperature	65 – 93	°C	
Back Pressure	0.17 – 0.34	MPa	
Screw Speed	30 – 60	rpm	
Maximum Moisture Content	0.12 – 0.2	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.