

LNPTTM THERMOCOMPTM COMPOUND EFB26ER

DESCRIPTION

LNP THERMOCOMP EFB26ER compound is based on Polyetherimide (PEI) resin containing 30% glass fiber, 10% glass bead. Added features of this grade include: Easy Molding, Mold Release.

GENERAL INFORMATION	
Features	Good Processability, Enhanced mold release, High stiffness/Strength, High temperature resistance
Fillers	Glass Fiber, Glass Bead
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	156	MPa	ISO 527
Tensile Stress, break, 5 mm/min	153	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.5	%	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	9000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	190	MPa	ISO 178
Flexural Stress, break, 2 mm/min	190	MPa	ISO 178
Flexural Strain, break, 2 mm/min	1.9	%	ISO 178
Flexural Modulus, 2 mm/min	10400	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	1.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	3.5E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	206	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	0.2	%	SABIC method
Density	1.61	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.27	%	ISO 62-1
INJECTION MOLDING ⁽³⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 365	°C	
Rear - Zone 1 Temperature	345 – 355	°C	
Middle - Zone 2 Temperature	355 – 365	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Nozzle Temperature	390 – 400	°C	
Mold Temperature	120 – 150	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.