

LNPTTM ELCRESTTM DMX1233CR

DESCRIPTION

LNP ELCRES DMX1233CR compound is a PC resin based transparent material with scratch resistance, chemical resistance, high flow and good ductility.

| GENERAL INFORMATION | |
|----------------------------|--|
| Features | Chemical Resistance, Scratch Resistance, Transparent/Translucent |
| Fillers | Unreinforced |
| Polymer Types | Polycarbonate (PC) |
| Processing Techniques | Injection Molding |
| INDUSTRY | SUB INDUSTRY |
| Automotive | Automotive Interiors |
| Electrical and Electronics | Electronic Components |

TYPICAL PROPERTY VALUES

Revision 20240318

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, brk, Type I, 50 mm/min | 45.2 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 55.6 | % | ASTM D638 |
| Tensile Modulus, 50 mm/min | 2098 | MPa | ASTM D638 |
| Flexural Strength, 1.3 mm/min, 50 mm span | 86.1 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 1910 | MPa | ASTM D790 |
| Tensile Stress, break, 50 mm/min | 45.4 | MPa | ISO 527 |
| Tensile Strain, break, 50 mm/min | 56.7 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2059 | MPa | ISO 527 |
| Flexural Strength, 2 mm/min | 83.5 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 1974 | MPa | ISO 178 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, notched, 23°C | 46.3 | J/m | ASTM D256 |
| Izod Impact, notched, -30°C | 27.3 | J/m | ASTM D256 |
| Izod Impact, unnotched, 23°C | NB | J/m | ASTM D4812 |
| Izod Impact, unnotched, -30°C | 1420 | J/m | ASTM D4812 |
| Izod Impact, notched 80*10*4 +23°C | 5.2 | kJ/m ² | ISO 180/1A |
| Izod Impact, unnotched 80*10*4 +23°C | NB | kJ/m ² | ISO 180/1U |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm | 4.89 | kJ/m ² | ISO 179/1eA |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| Instrumented Dart Impact Total Energy, 23°C | 61 | J | ASTM D3763 |
| Instrumented Dart Impact Ductility, 23°C | 100 | % | ASTM D3763 |
| THERMAL ⁽¹⁾ | | | |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 99 | °C | ASTM D648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 87.3 | °C | ASTM D648 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|----------|--------------|
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 100 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 87 | °C | ISO 75/Af |
| CTE, -40°C to 40°C, flow | 8.0E-5 | 1/°C | ASTM E831 |
| CTE, -40°C to 40°C, xflow | 8.0E-5 | 1/°C | ASTM E831 |
| CTE, -40°C to 40°C, flow | 7.9E-5 | 1/°C | ISO 11359-2 |
| CTE, -40°C to 40°C, xflow | 8.0E-5 | 1/°C | ISO 11359-2 |
| Vicat Softening Temp, Rate B/120 | 107 | °C | ASTM D1525 |
| Vicat Softening Temp, Rate B/120 | 108 | °C | ISO 306 |
| PHYSICAL ⁽¹⁾ | | | |
| Specific Gravity | 1.17 | - | ASTM D792 |
| Melt Flow Rate, 270°C/1.2 kgf | 11.8 | g/10 min | ASTM D1238 |
| Melt Flow Rate, 280°C/1.2 kgf | 16.6 | g/10 min | ASTM D1238 |
| Melt Flow Rate, 300°C/1.2 kgf | 44.6 | g/10 min | ASTM D1238 |
| Moisture Absorption, (23°C/50% RH/24hrs) | 0.21 | % | ISO 62-4 |
| Mold Shrinkage, flow ⁽²⁾ | 0.83 | % | SABIC method |
| Mold Shrinkage, xflow ⁽²⁾ | 0.9 | % | SABIC method |
| OPTICAL ⁽¹⁾ | | | |
| Light Transmission | | | |
| 1.0 mm | 90.2 | % | ASTM D1003 |
| 2.0 mm | 87.9 | % | ASTM D1003 |
| Haze, 1.0 mm | 1.2 | % | ASTM D1003 |
| Haze, 2.0 mm | 1.9 | % | ASTM D1003 |
| ELECTRICAL ⁽¹⁾ | | | |
| Surface Resistivity | 1.7E+17 | Ω | ASTM D257 |
| Volume Resistivity | 3.08E+16 | Ω.cm | ASTM D257 |
| Dielectric Constant, 1.1 GHz | 2.82 | - | SABIC method |
| Dissipation Factor, 1.1 GHz | 0.00972 | - | SABIC method |
| Dielectric Constant, 1.9 GHz | 2.83 | - | SABIC method |
| Dissipation Factor, 1.9 GHz | 0.01045 | - | SABIC method |
| Dielectric Constant, 5 GHz | 2.8 | - | SABIC method |
| Dissipation Factor, 5 GHz | 0.01206 | - | SABIC method |
| Dielectric Constant, 10 GHz | 2.81 | - | SABIC method |
| Dissipation Factor, 10 GHz | 0.01288 | - | SABIC method |
| Dielectric Constant, 20 GHz | 2.64 | - | SABIC method |
| Dissipation Factor, 20 GHz | 0.01255 | - | SABIC method |
| INJECTION MOLDING ⁽³⁾ | | | |
| Drying Temperature | 75 – 80 | °C | |
| Drying Time | 5 – 6 | Hrs | |
| Melt Temperature | 250 – 280 | °C | |
| Nozzle Temperature | 250 – 280 | °C | |
| Front - Zone 3 Temperature | 250 – 280 | °C | |
| Middle - Zone 2 Temperature | 250 – 280 | °C | |
| Rear - Zone 1 Temperature | 250 – 280 | °C | |
| Mold Temperature | 50 – 60 | °C | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.