

ULTEM™ RESIN DU319

DESCRIPTION

Transparent Polyetherimide blend with PET resin. Material is RoHS compliant and is also US FDA and EU Food Contact Compliant in recognized colors.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	110	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	82	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	60	%	ASTM D638
Tensile Modulus, 5 mm/min	3370	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	165	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	110	MPa	ISO 527
Tensile Stress, break, 5 mm/min	75	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	36	%	ISO 527
Tensile Modulus, 1 mm/min	3300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	155	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	26	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	950	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	40	J	ASTM D3763
Izod Impact, notched 80°10'4 +23°C	4	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	4	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	3	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	181	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	165	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.86E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	4.86E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	177	°C	ISO 306
Vicat Softening Temp, Rate B/120	180	°C	ISO 306
PHYSICAL			
Specific Gravity	1.29	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.7	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	8.1	g/10 min	ASTM D1238
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.17	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4 – 8	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 330	°C	
Nozzle Temperature	300 – 330	°C	
Front - Zone 3 Temperature	295 – 325	°C	
Middle - Zone 2 Temperature	290 – 320	°C	
Rear - Zone 1 Temperature	280 – 315	°C	
Mold Temperature	95 – 150	°C	
Back Pressure	0.7 – 1.4	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.