

LNPTM STAT-LOYTM COMPOUND 9X03508

EXCP0218

DESCRIPTION

LNP STAT-LOY 9X03508 compound is based on Polyphenylene Ether (PPE) / Nylon 6/6 blend containing proprietary fillers and glass fiber. Added features of this grade include: Permanently Anti-Static, Flame Retardant, High Impact.

GENERAL INFORMATION	
Features	Flame Retardant, Antistatic, Impact resistant
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	53	MPa	ASTM D638
Tensile Stress, break	53	MPa	ASTM D638
Tensile Strain, yield	2.1	%	ASTM D638
Tensile Strain, break	2.2	%	ASTM D638
Tensile Modulus, 50 mm/min	4820	MPa	ASTM D638
Flexural Stress	82	MPa	ASTM D790
Flexural Modulus	3440	MPa	ASTM D790
Tensile Stress, yield	59	MPa	ISO 527
Tensile Stress, break	58	MPa	ISO 527
Tensile Strain, yield	2.4	%	ISO 527
Tensile Strain, break	2.8	%	ISO 527
Tensile Modulus, 1 mm/min	4470	MPa	ISO 527
Flexural Stress	96	MPa	ISO 178
Flexural Modulus	4000	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	427	J/m	ASTM D4812
Izod Impact, notched, 23°C	37	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	8	J	ASTM D3763
Multiaxial Impact	1	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	230	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	186	°C	ASTM D648
CTE, -40°C to 40°C, flow	4.32E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.48E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	4.30E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.50E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	218	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	179	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.31	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.9	%	ASTM D570
Density	1.31	g/cm ³	ISO 1183
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽²⁾	1.E+10 – 1.E+12	Ω	ASTM D257
FLAME CHARACTERISTICS ⁽³⁾			
UL Yellow Card Link	E121562-101284110	-	-
UL Recognized, 94V-1 Flame Class Rating	2.4	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	200 – 230	°C	
Front - Zone 3 Temperature	220 – 230	°C	
Middle - Zone 2 Temperature	210 – 220	°C	
Rear - Zone 1 Temperature	200 – 210	°C	
Mold Temperature	40 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurement meets requirements as specified in ASTM D4496.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.