سابک ےناہے

NORYL GTXTM RESIN APS430

REGION ASIA

DESCRIPTION

NORYL GTX™ APS430 resin is a 30% glass reinforced alloy of Polyphenylene Ether (PPE) + Polyphenylene Sulfide (PPS). This injection moldable grade has a UL V0 flame rating, non-brominated, non-chlorinated FR, high stiffness, excellent chemical resistance, and high heat resistance. NORYL GTX APS430 resin is an excellent candidate for electrical and lighting connector applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	122	MPa	SABIC - Japan Method
Tensile Strain, break	10	%	SABIC - Japan Method
Flexural Stress	166	MPa	ASTM D790
Flexural Modulus	8620	MPa	ASTM D790
ІМРАСТ			
Izod Impact, notched, 23°C	78	J/m	ASTM D256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	255	°C	ASTM D648
CTE, -30°C to 30°C	1.8E-05 – 5.8E-05	1/°C	TMA
PHYSICAL			
Specific Gravity	1.48	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.02	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	43.6	g/10 min	ASTM D1238
ELECTRICAL			
Surface Resistivity	1.E+16	Ω	ASTM D257
Relative Permittivity, 50/60 Hz	3.3	-	ASTM D150
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	<u>E45587-100154477</u>	-	
UL Recognized, 94V-0 Flame Class Rating	≥0.8	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	2 – 5	Hrs	
Melt Temperature	290 – 310	°C	
Rear - Zone 1 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	280 – 310	°C	
Front - Zone 3 Temperature	280 – 310	°C	
Nozzle Temperature	290 - 310	°C	
Mold Temperature	120 – 140	°C	
Screw Speed	40 - 60	rpm	
Back pressure (Plastic Pressure)	5 – 14	MPa	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS

Revision 20231109



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.