

NORYL GTX™ RESIN SOLUTIONS FOR NEW WHEEL INSERT DESIGNS

Design freedom and lightweight performance

Automotive designers look for new ways to stand out from the crowds with aesthetically appealing designs and outstanding technical performance. Lightweight, injection molded parts offer design freedom...from special editions to exciting new designs.

NORYL GTX™ resin is an alloy of polyphenylene ether (PPE) and polyamide (PA), combining the inherent properties of PPE (long-term dimensional stability, very low moisture absorption, stiffness, strength, impact resistance) with the chemical resistance and flow of PA.

This advanced thermoplastic allows for new concept designs while providing superior mechanical properties and lightweight solutions that can withstand tough environments.



KEY PROPERTIES

- High heat resistance: to withstand heat build-up in brake or recuperation systems.
- Paintability.
- Impact resistance to enhance crash performance.
- Very low specific gravity for reduced part weight and optimized moment of inertia.

NORYL Resin Grade	Feature	E-Modulus (DIN527)	HDT (0,45 MPa)	Vicat A/50	MVR (ISO 1133)	Charpy (RT notched)
GTX902(E)	Standard	2200 Mpa	150°C	~215°C	12 cm ³ /10min	13 kJ/mm ²
GTX910	High temperature	2200 MPa	175°C	238°C	10 cm ³ /10min	25 kJ/mm ²
GTX914	High impact	2100 Mpa	180°C	245°C	12 cm ³ /10min	30 kJ/mm ²
GTX973	Electrostatic painting	2300 Mpa	195°C	~250°C	12 cm ³ /10min	15 kJ/mm ²
GTX964	Low temp impact	2000 MPa	175°C	240°C	7 cm ³ /10min	30 kJ/mm ²



CONTACT DETAILS:

AMERICAS

SABIC Americas
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
T +1 713 430 2301

NORYL™ RESIN

Stacy Cashin
stacy.cashin@sabic.com

ASIA PACIFIC

SABIC Shanghai
2550 Xiupu Road, Pudong
Shanghai 201319
China
T +86-21-2037-8188

NORYL™ RESIN

Sung Bae Choi
sung-bae.choi@sabic.com

EUROPE

SABIC Bergen op Zoom
Plasticslaan 1
4612 PX Bergen op Zoom
The Netherlands
T +31 164 292 911

NORYL™ RESIN

Marcel Verhagen
marcel.verhagen@sabic.com

DISCLAIMER: Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2020 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.