LNP™ ELCRIN™ RCX7236

DESCRIPTION

RCX7236 is an impact modified Polycarbonate (PC) containing 60% PCR content with non-brominated and non-chlorinated FR intended for thin-wall applications requiring excellent impact/flow balance performance. It's available for custom color matching.

GENERAL INFORMATION	
Features	High Flow, Thin Wall, Non Cl/Br flame retardant, Impact resistant
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding
Regional Availability	Global

INDUSTRY	SUB INDUSTRY
Consumer	Consumer Goods
Electrical and Electronics	Electronic Components

TYPICAL PROPERTY VALUES

Revision 20250225

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	55	MPa	ASTM D638
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	2500	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D790
IMPACT [1]			
Izod Impact, notched 80*10*4 +23°C	38	kJ/m²	ISO 180/1A
Izod Impact, notched, 23°C	650	J/m	ASTM D256
Izod Impact, notched, -30°C	120	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	61	J	ASTM D3763
THERMAL [1]			
HDT, 1.82 MPa, 3.2mm, unannealed	90	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	101	°C	ASTM D648
Vicat Softening Temp, Rate B/50	107	°C	ASTM D1525
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E831
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL [1]			

© 2025 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, (23°C/saturated)	0.12	%	ISO 62-1
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow [2]	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	18	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 260°C/2.16 kg	16.8	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS [3]			
UL Recognized, 94V-0 Flame Class Rating	≥1.0	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
UL Yellow Card Link	UL Yellow Card	-	-
INJECTION MOLDING [4]			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	.02	%	
Hopper Temperature	60 – 80	°C	
Melt Temperature	250 – 300	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Middle - Zone 2 Temperature	240 – 290	°C	
Front - Zone 3 Temperature	250 – 300	°C	
Nozzle Temperature	250 – 300	°C	
Mold Temperature	60 – 85	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2025 Copyright by SABIC. All rights reserved