LNP™ THERMOCOMP™ Compound KZ006AXP

DESCRIPTION

LNP THERMOCOMP KZ006AXP compound is based on POM (Acetal) homopolymer resin containing 30% milled glass.

GENERAL INFORMATION	
Features	Low Warpage, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Acetal (POM) Homopolymer
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Flexural Strength, 1.3 mm/min, 50 mm span	72	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4150	MPa	ASTM D790
Tensile Stress, brk, Type I, 5 mm/min	45	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D638
IMPACT [1]			
Izod Impact, unnotched, 23°C	180	J/m	ASTM D4812
Izod Impact, notched, 23°C	38	J/m	ASTM D256
THERMAL [1]			
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D648
PHYSICAL [1]			
Density	1.64	g/cm³	ASTM D792
Mold Shrinkage, flow, 24 hrs [2]	0.8 – 1	%	ASTM D955
Water Absorption, (23°C/24hrs)	0.3	%	ASTM D570
INJECTION MOLDING [3]			
Drying Temperature	90	°C	
Drying Time	4	Hrs	
Melt Temperature	200 – 215	°C	
Mold Temperature	85 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	

© 2026 Copyright by SABIC. All rights reserved

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved