LNP™ ELCRES™ FXG9111T

DESCRIPTION

ELCRES FXG9111T is PC-Siloxane copolymer in special "Diamond" appearance, which is part of the VISUALFX product family. This product features vivid and resplendent look with improved ductility and medium flow. FR V0 at 2mm. Color package may affect performance. Applications include housing of consumer electronics, cosmetic packaging, automotive interior decoration, etc.

GENERAL INFORMATION	
Features	Flame Retardant, Aesthetics/Visual effects, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Interiors
Consumer	Home Appliances, Commercial Appliance
Electrical and Electronics	Electrical Devices and Displays
Packaging	Consumer Packaging

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	44	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	55	%	ASTM D638
Tensile Modulus, 50 mm/min	2162	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	89	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	87	MPa	ASTM D790
Flexural Stress at 5% strain, 1.3 mm/min, 50 mm span	84	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2220	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	70	%	ISO 527
Tensile Modulus, 1 mm/min	2166	MPa	ISO 527
Flexural Stress at 3.5% strain, 2 mm/min	67.3	MPa	ISO 178
Flexural Strain, break, 2 mm/min	7.9	%	ISO 178
Flexural Strength, 2 mm/min	86.1	MPa	ISO 178
Flexural Modulus, 2 mm/min	2202	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	2140	J/m	ASTM D4812

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched, 0°C	500	J/m	ASTM D256
Izod Impact, notched, 23°C	718	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	53	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	182	kJ/m²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	59	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	133	kJ/m²	ISO 179/1eU
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	119	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	107	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	119	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	107	°C	ISO 75/Af
CTE, -40°C to 95°C, flow	7.6E-05	1/°C	ASTM E831
CTE, -40°C to 95°C, xflow	8.5E-05	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	8.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.2E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	131	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	125	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	126	°C	ISO 306
Relative Temp Index, Elec [2]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	80	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.2	-	ASTM D792
Density	1.196	g/cm³	ISO 1183
Water Absorption, (23°C/24hrs)	0.10	%	ISO 62-1
Moisture Absorption, (23°C/50% RH/24hrs)	0.04	%	ISO 62-4
Melt Flow Rate, 300°C/1.2 kgf	16.2	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/1.2 kg	15.2	cm³/10 min	ASTM D1238
Mold Shrinkage, flow [3]	0.53	%	SABIC method
Mold Shrinkage, xflow [3]	0.58	%	SABIC method
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-104583633	-	-
UL Recognized, 94V-0 Flame Class Rating	≥2.0	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	90	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 285	°C	
Nozzle Temperature	250 – 285	°C	
Front - Zone 3 Temperature	250 – 285	°C	
Middle - Zone 2 Temperature	250 – 285	°C	
Rear - Zone 1 Temperature	250 – 285	°C	
Mold Temperature	50 – 90	°C	

© 2026 Copyright by SABIC. All rights reserved

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved