LNP™ THERMOCOMP™ COMPOUND JF004E

JF-1004 EM
REGION EUROPE

DESCRIPTION

LNP THERMOCOMP JF004E compound is based on Polyethersulfone (PES) resin containing 20% glass fiber. Added features of this grade include: Easy Molding.

GENERAL INFORMATION	
Features	Good Processability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyethersulfone (PESU)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break, 5 mm/min	128	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	7350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	178	MPa	ISO 178
Flexural Modulus, 2 mm/min	6000	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL [1]			
CTE, 23°C to 60°C, flow	2.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.5E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	223	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	218	°C	ISO 75/Af
Relative Temp Index, Elec	180	°C	UL 746B
Relative Temp Index, Mech w/impact	180	°C	UL 746B
Relative Temp Index, Mech w/o impact	180	°C	UL 746B
PHYSICAL [1]			
Mold Shrinkage on Tensile Bar, flow [2]	0.25 – 0.45	%	SABIC method
Density	1.51	g/cm³	ISO 1183

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS [3]			
UL Yellow Card Link	E45329-101283859	-	-
UL Recognized, 94V-0 Flame Class Rating	0.81	mm	UL 94

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved