

# LNPT<sup>™</sup> COLORCOMP<sup>™</sup> COMPOUND N1000EXB

## DESCRIPTION

LNP COLORCOMP N1000EXB compound is based on unfilled Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend. Added features of this grade include: Good Flow and Excellent Impact, Healthcare, Low Extractables, Biocompatible (ISO10993 or USP Class VI).

GENERAL INFORMATION	
Features	Good Processability, Aesthetics/Visual effects, Biocompatibility-ISO10993, Food contact, Healthcare/Formulation lock, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Water Management
Consumer	Home Appliances
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Packaging	Industrial Packaging, Food & Beverage

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 5 mm/min	2270	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	63	mg/1000cy	ASTM D1044
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	100	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Ball Indentation Hardness, H358/30	96	MPa	ISO 2039-1
Hardness, Rockwell R	115	-	ISO 2039-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	580	J/m	ASTM D256
Izod Impact, notched, -30°C	480	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	54	J	ASTM D3763
Izod Impact, notched 80*10*3 +23°C	50	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	30	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	50	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	30	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL <sup>(1)</sup></b>			
Vicat Softening Temp, Rate B/50	130	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	112	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ASTM E831
Thermal Conductivity	0.2	W/m.°C	ISO 8302
CTE, 23°C to 60°C, flow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C, by VDE	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	126	°C	ISO 306
Vicat Softening Temp, Rate B/120	128	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	102	°C	ISO 75/Ae
Relative Temp Index, Elec <sup>(2)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	105	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.15	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow <sup>(3)</sup>	0.5 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	24	g/10 min	ASTM D1238
Density	1.15	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.6	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	8	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	22	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.007	-	IEC 60250
Comparative Tracking Index <sup>(4)</sup>	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.2	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥1.2	mm	UL 746A
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-103956764</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
Glow Wire Flammability Index, 3.5 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.5 mm	725	°C	IEC 60695-2-13
Oxygen Index (LOI)	23	%	ISO 4589
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	100-110	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Nozzle Temperature	240 – 280	°C	
Melt Temperature	260 – 290	°C	
Front - Zone 3 Temperature	250 – 290	°C	
Middle - Zone 2 Temperature	250 – 290	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Value shown here is based on internal measurement.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.