LNP™ ELCRIN™ RCM6337

DESCRIPTION

LNP ELCRIN RCM6337 is an injection moldable filled PC/ABS with non-brominated and non-chlorinated flame retardant. It contains 65% post consumer recycle content with a UL94 V0 rating 1.0mm. Developed for thin Wall applications that require high ductility and high stiffness performance.

GENERAL INFORMATION	
Features	Non Cl/Br flame retardant, Dimensional stability, High stiffness/Strength
Fillers	Talc
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Home Appliances, Commercial Appliance

TYPICAL PROPERTY VALUES

Revision 20250606

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 5 mm/min	58	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	50	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	>70	%	ASTM D638
Tensile Modulus			
1 mm/min	3160	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	96	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3020	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	58	MPa	ISO 527
Tensile Stress, break, 5 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.2	%	ISO 527
Tensile Strain, break, 5 mm/min	>70	%	ISO 527
Tensile Modulus, 1 mm/min	3160	MPa	ISO 527
Flexural Strength, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	3100	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	550	J/m	ASTM D256
Izod Impact, notched 80*10*3 +23°C	38	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	28	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	29	kJ/m²	ISO 179/1eA
Instrumented Dart Impact Total Energy, 23°C	55	J	ASTM D3763
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	102	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	93	°C	ASTM D648

© 2025 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	92	°C	ISO 75/Af
CTE			
23°C to 80°C, flow	7.0 – 8.0	1/°C	ISO 11359-2
23°C to 80°C, xflow	8.0 – 9.0	1/°C	ISO 11359-2
Relative Temp Index, Elec [2]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	80	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.22	-	ASTM D792
Melt Flow Rate, 260°C/2.16 kgf	12	g/10 min	ASTM D1238
Mold Shrinkage, flow, 3.2 mm [3]	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm [3]	0.5 – 0.7	%	SABIC method
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-104702404	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.0	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 285	°C	
Nozzle Temperature	245 – 285	°C	
Front - Zone 3 Temperature	245 – 285	°C	
Middle - Zone 2 Temperature	220 – 275	°C	
Rear - Zone 1 Temperature	220 – 265	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2025 Copyright by SABIC. All rights reserved