

ULTEM™ RESIN AUR210G6

REGION EUROPE

DESCRIPTION

AUR210G6 is a 30% glass fiber filled grade based on ULTEM recycle.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break, 5 mm/min	120	MPa	ISO 527
Tensile Modulus, 1 mm/min	7500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	180	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
THERMAL			
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	212	°C	ISO 75/Be
PHYSICAL			
Density	1.53	g/cm ³	ISO 1183
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.4	%	SABIC method
Melt Volume Rate, MVR at 337°C/6.7 kg	4.5	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	370 – 410	°C	
Nozzle Temperature	360 – 410	°C	
Front - Zone 3 Temperature	370 – 420	°C	
Middle - Zone 2 Temperature	360 – 410	°C	
Rear - Zone 1 Temperature	350 – 400	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.