

# LNPTM LUBRICOMPTM COMPOUND RFL26

RFL-4026

## DESCRIPTION

LNP LUBRICOMP RFL26 compound is based on Nylon 6/6 resin containing 30% glass fiber, 10% PTFE. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break	185	MPa	ASTM D638
Tensile Strain, break	3.3	%	ASTM D638
Flexural Stress	275	MPa	ASTM D790
Flexural Stress	262	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Multiaxial Impact	4	J	ISO 6603
<b>THERMAL <sup>(1)</sup></b>			
CTE, -40°C to 40°C, flow	3.E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	65	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.46	g/cm <sup>3</sup>	ASTM D792
Wear Factor Washer	6	10 <sup>-4</sup> -10 in <sup>3</sup> -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.61	-	ASTM D3702 Modified: Manual
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-101282712</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	80	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.