

LNPT[™] FARADEX[™] COMPOUND AX88130

EMI-X PDX-A-88130

DESCRIPTION

LNP FARADEX AX88130 compound is based on Acrylonitrile Butadiene Styrene (ABS) resin containing stainless steel fiber. Added features of this grade include: Electrically Conductive, EMI/RFI shielding.

GENERAL INFORMATION	
Features	Electrically Conductive, EMI/RFI Shielding, No PFAS intentionally added
Fillers	Stainless Steel Fiber
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components
Industrial	Electrical, Material Handling
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	52	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3 – 4	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	93	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3440	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	160 – 214	J/m	ASTM D4812
Izod Impact, notched, 23°C	58	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	93	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Specific Gravity	1.13	-	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.3	%	ASTM D570
Mold Shrinkage, 48 hrs @ 23°C, flow ⁽²⁾	0.5 – 0.5	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽³⁾	1.E+03	Ω	ASTM D257
Volume Resistivity	1.E+03	Ω.cm	IEC 60093
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.05 – 0.1	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	260	°C	
Front - Zone 3 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.