NORYL™ RESIN V0150TW

DESCRIPTION

NORYL V0150TW resin is an unreinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of V0 at 1.0mm, 5VA at 1.5mm along with a UL746C Outdoor Suitability rating of F1. NORYL V0150TW resin exhibits high impact strength, good dimensional stability, high heat resistance, strong electrical performance and very low specific gravity. NORYL V0150TW resin is intended for parts that are exposed to tough outdoor environments such as Solar / Photovoltaic (PV) junction boxes and micro-invertors, and other electrical components requiring thin wall frame retardant.

GENERAL INFORMATION	
Features	Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Non Cl/Br flame retardant, Dimensional stability, High stiffness/Strength, High temperature resistance, Low temperature impact
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Home Appliances, Commercial Appliance
Electrical and Electronics	Energy Management, Electronic Components, Mobile Phone - Computer - Tablets
Hydrocarbon and Energy	Energy Storage
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260202

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 5 mm/min	69	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	51	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	4.6	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	16	%	ASTM D638
Tensile Modulus, 5 mm/min	2584	MPa	ASTM D638
Flexural Stress at 5% strain, 1.3 mm/min, 50 mm span	108	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2590	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	70	MPa	ISO 527
Tensile Stress, break, 5 mm/min	51	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.5	%	ISO 527
Tensile Strain, break, 5 mm/min	24.7	%	ISO 527
Tensile Modulus, 1 mm/min	2614	MPa	ISO 527
Flexural Strength, 2 mm/min	117	MPa	ISO 178
Flexural Modulus, 2 mm/min	2556	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	202	J/m	ASTM D256
Izod Impact, notched, -30°C	86	J/m	ASTM D256

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched, 23°C	2160	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	1520	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	15.9	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7.9	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	131	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	115	kJ/m²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	18.4	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6.1	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	95	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	95	kJ/m²	ISO 179/1eU
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	149	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	133	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	149	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	131	°C	ISO 75/Af
Vicat Softening Temp, Rate A/50	165	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	153	°C	ASTM D1525
Vicat Softening Temp, Rate A/50	164	°C	ISO 306
Vicat Softening Temp, Rate B/50	153	°C	ISO 306
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.6E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.4E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec [2]	110	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	105	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	115	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.1	-	ASTM D792
Density	1.1	g/cm³	ISO 1183
Melt Flow Rate, 300°C/5.0 kgf	14.5	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/5.0 kg	10.7	cm³/10 min	ISO 1133
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Mold Shrinkage, flow, 3.2 mm [3]	1.01	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm [3]	1.08	%	SABIC method
ELECTRICAL [1]			
Volume Resistivity	2.0E+16	Ω.cm	ASTM D257
Surface Resistivity	1.1E+16	Ω	ASTM D257
Comparative Tracking Index (UL) {PLC} [2]	2	PLC Code	UL 746A
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-104649328	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.0	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	825	°C	IEC 60695-2-13
UV-light, water exposure/immersion	f1	-	UL 746C

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING [4]			
Drying Temperature	100 – 120	°C	
Drying Time	3 – 5	Hrs	
Melt Temperature	280 – 330	°C	
Nozzle Temperature	250 – 330	°C	
Front - Zone 3 Temperature	280 – 330	°C	
Middle - Zone 2 Temperature	280 – 330	°C	
Rear - Zone 1 Temperature	280 – 330	°C	
Hopper Temperature	70 – 140	°C	
Mold Temperature	30 – 100	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved