

# LNPT<sup>TM</sup> ELCREST<sup>TM</sup> FST2734E

## DESCRIPTION

LNP ELCRES FST2734E is a glass fiber reinforced Polycarbonate (PC) Copolymer Resin for sheet extrusion and part production by thermoforming processes. This UV stabilized, flame retardant resin with no intentionally-added PFAS, is intended for train interior applications requiring EN 45545 R1–HL2 compliant materials (e.g. side panels & partition walls). Available in opaque colors.

GENERAL INFORMATION	
Features	Good Processability, Low Smoke and Toxicity, High stiffness/Strength, Weatherable/UV stable, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Extrusion
INDUSTRY	SUB INDUSTRY
Mass Transportation	Rail

## TYPICAL PROPERTY VALUES

Revision 20240620

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Modulus, 1 mm/min	4600	MPa	ISO 527
Tensile Stress, yield, 5 mm/min	57	MPa	ISO 527
Tensile Stress, break, 5 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Nominal Strain, break, 5 mm/min	7	%	ISO 527
Flexural Modulus, 2 mm/min	4650	MPa	ISO 178
Flexural Strength, 2 mm/min	100	MPa	ISO 178
Flexural Strain, break, 2 mm/min	9	%	ISO 178
Flexural Stress at 3.5% strain, 2 mm/min	90	MPa	ISO 178
Tensile Modulus, 5 mm/min	4600	MPa	ASTM D638
Tensile Stress, yld, Type I, 5 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	50	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D638
Tensile Nominal Strain, brk, Type I, 5 mm/min	6	%	ASTM D638
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched 80*10*4 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*3 +23°C	70	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	60	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	55	kJ/m <sup>2</sup>	ISO 179/1eU

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched, 23°C	70	J/m	ASTM D256
Izod Impact, unnotched, 23°C	650	J/m	ASTM D4812
<b>THERMAL <sup>(1)</sup></b>			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	120	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	127	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	128	°C	ISO 306
Vicat Softening Temp, Rate B/120	129	°C	ISO 306
CTE, -40°C to 90°C, flow	3.5E-5	1/°C	ISO 11359-2
CTE, -40°C to 90°C, xflow	6.8E-5	1/°C	ISO 11359-2
HDT, 1.82 MPa, 3.2mm, unannealed	119	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	128	°C	ASTM D648
Ball Pressure Test, 125°C +/- 2°C	PASS	-	IEC 60695-10-2
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.41	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	8.5	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/2.16 kg	3.5	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/1.2 kg	8.5	cm <sup>3</sup> /10 min	ISO 1133
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Water Absorption, (23°C/24hrs)	0.12	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.2	%	ISO 62-1
Specific Gravity	1.42	-	ASTM D792
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
Smoke density, DS-4, 50 kW/m <sup>2</sup> <sup>(2)</sup>	<300	-	ISO 5659-2
Smoke density, VOF4, 50 kW/m <sup>2</sup> <sup>(2)</sup>	<600	-	ISO 5659-2
Smoke toxicity, CITG (8 min), 50 kW/m <sup>2</sup> <sup>(2)</sup>	<0.9	-	ISO 5659-2
Heat release, MAHRE, 50 kW/m <sup>2</sup> <sup>(2)</sup>	<90	kW/m <sup>2</sup>	ISO 5660-1
Lateral Flame Spread, CFE	>20	kW/m <sup>2</sup>	ISO 5658-2
Fire Safety Hazard Level - Requirement set R1 <sup>(2) (3)</sup>	HL2	-	EN 45545-2
<b>SHEET EXTRUSION</b>			
Drying Temperature	90 – 110	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	18	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	220 – 260	°C	
Barrel - Zone 1 Temperature	180 – 210	°C	
Barrel - Zone 2 Temperature	200 – 230	°C	
Barrel - Zone 3 Temperature	220 – 260	°C	
Barrel - Zone 4 Temperature	220 – 260	°C	
Die Temperature	220 – 260	°C	
Roll Stack Temp - Bottom	90 – 120	°C	
Roll Stack Temp - Middle	90 – 120	°C	
Roll Stack Temp - Top	90 – 120	°C	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) 2 to 4 mm
- (3) based on EN 45545-2: 2020 revision

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.