

LNPTTM LUBRICOMPTM COMPOUND AI001

DESCRIPTION

LNP LUBRICOMP AI001 compound is based on Acrylonitrile Butadiene Styrene (ABS) resin containing silicone. Added feature of this material is: Internally lubricated, Easy molding, Wear Resistant.

GENERAL INFORMATION	
Features	Good Processability, Wear resistant, No PFAS intentionally added
Fillers	Unreinforced, Silicone
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding, Extrusion

INDUSTRY	SUB INDUSTRY
Consumer	Home Decoration
Electrical and Electronics	Electrical Components and Infrastructure

TYPICAL PROPERTY VALUES

Revision 20240913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Flexural Modulus, 1.3 mm/min, 50 mm span	2240	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	63	MPa	ASTM D790
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Flexural Stress	62	MPa	ISO 178
Tensile Modulus, 50 mm/min	2140	MPa	ASTM D638
Tensile Stress, yld, Type I, 50 mm/min	42	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	31	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	2.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	23	%	ASTM D638
Tensile Modulus, 1 mm/min	2120	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	40	MPa	ISO 527
Tensile Stress, break, 50 mm/min	31	MPa	ISO 527
Tensile Strain, break, 50 mm/min	2.4	%	ISO 527
Tensile Nominal Strain, break, 50 mm/min	30	%	ISO 527
IMPACT ⁽¹⁾			
Charpy Impact, notched, 23°C	25	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, 23°C	NB	kJ/m ²	ISO 179/2C
Izod Impact, notched, 23°C	290	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1700	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 0°C	19	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 0°C	120	kJ/m ²	ISO 180/1U

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 -30°C	110	kJ/m ²	ISO 180/1U
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	76	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	92	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	81	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	90	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	97	°C	ISO 306
Vicat Softening Temp, Rate B/120	98	°C	ISO 306
CTE, -40°C to 40°C, flow	9.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.8E-05	1/°C	ISO 11359-2
PHYSICAL ⁽¹⁾			
Density	1.04	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 230°C/5.0 kg	11	cm ³ /10 min	ISO 1133
Melt Flow Rate, 230°C/5 kgf	11	g/10 min	ASTM D1238
Moisture Absorption, (23°C/50% RH/24hrs)	0.2	%	ISO 62-4
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.2	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.6	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.8	%	ISO 62-1
Mold Shrinkage, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow	0.7 – 0.9	%	SABIC method
Dynamic COF	0.3	-	ASTM D3702 Modified: Manual
Static COF	0.4	-	ASTM D3702 Modified: Manual
Wear Factor Washer	13	10 ⁻¹⁰ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
INJECTION MOLDING ⁽²⁾			
Drying Time	2 – 4	Hrs	
Drying Temperature	80	°C	
Maximum Moisture Content	0.05 – 0.1	%	
Hopper Temperature	40	°C	
Melt Temperature	250 – 260	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Middle - Zone 2 Temperature	240 – 260	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Nozzle Temperature	250 – 270	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw speed (Circumferential speed)	0.15 – 0.25	m/s	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.