

SILTEM™ RESIN STM1600

REGION EUROPE

DESCRIPTION

SILTEM™ STM1600 resin is a flexible polyetherimide(PEI)-siloxane copolymer designed for wire and cable applications. The material is RoHS compliant and offers a halogen free (according VDE 0472) flame retardant solution that also offers low smoke emission and toxicity. It is an amber colored transparent material that can be selfcolored and easily processed on conventional processing equipment. The material may also be used for extrusion of e.g. corrugated pipes and profiles as well as flexible injection molded parts.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

INDUSTRY	SUB INDUSTRY
Automotive	Aerospace
Electrical and Electronics	Energy Management
Industrial	Electrical, Material Handling, Defense
Mass Transportation	Rail

TYPICAL PROPERTY VALUES

Revision 20231113

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Hardness, Shore D	72	-	ASTM D2240
Taber Abrasion, CS-17, 1 kg	50	mg/1000cy	ASTM D1044
Tensile Stress, yield, 50 mm/min	42	MPa	ISO 527
Tensile Stress, break, 50 mm/min	41	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	10	%	ISO 527
Tensile Strain, break, 50 mm/min	74	%	ISO 527
Tensile Modulus, 1 mm/min	1380	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	55	MPa	ISO 178
Flexural Modulus, 2 mm/min	1250	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	36	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	25	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/120	167	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	144	°C	ISO 75/Bf
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.86 – 1.01	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	8.6	g/10 min	ASTM D1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.58	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.58	%	ISO 62-1
Matrix Tg	195	°C	DMA
ELECTRICAL			
Volume Resistivity	>1.E+16	Ω.cm	ASTM D257

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity	>1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	16.6	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	3.14	-	ASTM D150
Relative Permittivity, 100 kHz	3	-	ASTM D150
Relative Permittivity, 1 MHz	3.02	-	ASTM D150
Dissipation Factor, 100 Hz	0.014	-	ASTM D150
Dissipation Factor, 100 kHz	0.0064	-	ASTM D150
Dissipation Factor, 1 MHz	0.0055	-	ASTM D150
Comparative Tracking Index	175	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Oxygen Index (LOI)	48	%	ASTM D2863
INJECTION MOLDING			
Drying Temperature	105	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 320	°C	
Nozzle Temperature	310 – 320	°C	
Front - Zone 3 Temperature	310 – 320	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	310 – 320	°C	
Mold Temperature	105 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.