

# ULTEM™ RESIN 2212R

REGION EUROPE

## DESCRIPTION

20% Milled glass filled, enhanced flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

| INDUSTRY                   | SUB INDUSTRY  |
|----------------------------|---|
| Automotive                 | Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles  |
| Building and Construction  | Building Component, Water Management  |
| Consumer                   | Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture   |
| Electrical and Electronics | Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication |
| Hygiene and Healthcare     | Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing                                  |
| Industrial                 | Electrical, Material Handling, Textile, Eyewear   |
| Mass Transportation        | Rail  |
| Packaging                  | Industrial Packaging  |

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES  | TYPICAL VALUES | UNITS             | TEST METHODS |
|---|----------------|-------------------|--------------|
| <b>MECHANICAL</b>                                   |                |                   |              |
| Tensile Stress, break, 5 mm/min                     | 75             | MPa               | ISO 527      |
| Tensile Strain, break, 5 mm/min                     | 8              | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min                           | 4500           | MPa               | ISO 527      |
| Flexural Stress, yield, 2 mm/min                    | 135            | MPa               | ISO 178      |
| <b>IMPACT</b>                                       |                |                   |              |
| Izod Impact, unnotched 80*10*4 +23°C                | 30             | kJ/m <sup>2</sup> | ISO 180/1U   |
| <b>THERMAL</b>                                      |                |                   |              |
| Thermal Conductivity                                | 0.28           | W/m·°C            | ISO 8302     |
| Vicat Softening Temp, Rate B/120                    | 211            | °C                | ISO 306      |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm             | 202            | °C                | ISO 75/Be    |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm             | 189            | °C                | ISO 75/Ae    |
| CTE, -40°C to 150°C, flow                           | 3.7E-05        | 1/°C              | ISO 11359-2  |
| CTE, -40°C to 150°C, xflow                          | 4.7E-05        | 1/°C              | ISO 11359-2  |
| Relative Temp Index, Elec <sup>(1)</sup>            | 170            | °C                | UL 746B      |
| Relative Temp Index, Mech w/impact <sup>(1)</sup>   | 170            | °C                | UL 746B      |
| Relative Temp Index, Mech w/o impact <sup>(1)</sup> | 170            | °C                | UL 746B      |
| <b>PHYSICAL</b>                                     |                |                   |              |
| Mold Shrinkage on Tensile Bar, flow                 | 0.3 – 0.5      | %                 | SABIC method |
| Density   | 1.43           | g/cm <sup>3</sup> | ISO 1183     |
| <b>ELECTRICAL</b>                                   |                |                   |              |
| Comparative Tracking Index (UL) {PLC}               | 4              | PLC Code          | UL 746A      |

| PROPERTIES                                  | TYPICAL VALUES                 | UNITS    | TEST METHODS   |
|---|--------------------------------|----------|----------------|
| Hot-Wire Ignition (HWI), PLC 1              | ≥3                             | mm       | UL 746A        |
| Hot-Wire Ignition (HWI), PLC 2              | ≥1.5                           | mm       | UL 746A        |
| High Amp Arc Ignition (HAI), PLC 3          | ≥3                             | mm       | UL 746A        |
| High Amp Arc Ignition (HAI), PLC 4          | ≥1.5                           | mm       | UL 746A        |
| High Voltage Arc Track Rate {PLC}           | 2                              | PLC Code | UL 746A        |
| Arc Resistance, Tungsten {PLC}              | 7                              | PLC Code | ASTM D495      |
| <b>FLAME CHARACTERISTICS <sup>(1)</sup></b> |                                |          |                |
| UL Yellow Card Link                         | <a href="#">E121562-221097</a> | -        | -              |
| Glow Wire Flammability Index, 1.5 mm        | 960                            | °C       | IEC 60695-2-12 |
| Glow Wire Ignitability Temperature, 1.5 mm  | 875                            | °C       | IEC 60695-2-13 |
| UL Recognized, 94V-0 Flame Class Rating     | ≥0.41                          | mm       | UL 94          |
| <b>INJECTION MOLDING</b>                    |                                |          |                |
| Drying Temperature                          | 150                            | °C       |                |
| Drying Time                                 | 4 – 6                          | Hrs      |                |
| Maximum Moisture Content                    | 0.02                           | %        |                |
| Melt Temperature                            | 360 – 400                      | °C       |                |
| Nozzle Temperature                          | 360 – 400                      | °C       |                |
| Front - Zone 3 Temperature                  | 370 – 410                      | °C       |                |
| Middle - Zone 2 Temperature                 | 360 – 400                      | °C       |                |
| Rear - Zone 1 Temperature                   | 340 – 380                      | °C       |                |
| Hopper Temperature                          | 80 – 100                       | °C       |                |
| Mold Temperature                            | 140 – 180                      | °C       |                |

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.