

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND KF004

KF-1004

REGION EUROPE

## DESCRIPTION

LNP THERMOCOMP KF004 compound is based on POM (Acetal) copolymer resin containing 20% glass fiber.

GENERAL INFORMATION	
Features	High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Acetal (POM) Copolymer
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break, 5 mm/min	104	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.3	%	ISO 527
Tensile Modulus, 1 mm/min	7200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	122	MPa	ISO 178
Flexural Modulus, 2 mm/min	5500	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched 80*10*4 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
CTE, 23°C to 60°C, flow	6.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.07E-04	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	157	°C	ISO 75/Af
<b>PHYSICAL <sup>(1)</sup></b>			
Mold Shrinkage, flow <sup>(2)</sup>	0.5	%	SABIC method
Density	1.54	g/cm <sup>3</sup>	ISO 1183
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	200 – 215	°C	
Front - Zone 3 Temperature	210 – 220	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	195 – 205	°C	
Rear - Zone 1 Temperature	175 – 190	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.