SA9000

DESCRIPTION

NORYL™ SA9000 resin is a modified, low molecular weight, bi-functional oligomer based on polyphenylene ether (PPE) with vinyl end-groups. It is well suited for use with other unsaturated monomers and resins which cure via free radical reactions. These include styrenic, allylic, acrylic, maleimide, methacrylic, and unsaturated polyesters monomers and resins. It has a low solution viscosity and outstanding solubility in toluene & methyl ethyl ketone (MEK). Key application areas are in electronic packaging which include PCB laminates, copper clad laminates, non-epoxy prepregs, and adhesives. The use of NORYL SA9000 is especially advantageous in insulating materials where very low dielectric properties and decreased moisture absorption are required.

TYPICAL PROPERTY VALUES

Revision 20260402

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL			
Tg (half width)	160	°C	SABIC method
PHYSICAL			
Specific Gravity	1.02	-	ASTM D792
Physical Form	POWDER	-	SABIC method
Intrinsic Viscosity	0.09	dl/g	SABIC method
Phenolic End-group Content	- 300	ppm	SABIC method
Vinyl Functionality	1.9	-	SABIC method
Solubility, Toluene (21°C)	50	Wt. %	SABIC method
Solubility, Methyl Ethyl Ketone (21°C)	50	Wt. %	SABIC method
Mn	2300	-	SABIC method
Viscosity, 50 wt% in toluene, 25°C	298	cP	SABIC method
Viscosity, 50 wt% in methyl ethyl ketone, 25°C	160	cP	SABIC method
ELECTRICAL			
Dielectric Constant			
1 MHz	2.54	-	ASTM D150
Dissipation Factor			
1 MHz	0.0007	-	ASTM D150

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved