

# LNPTM STAT-KONTM COMPOUND ZD000XXR

## DESCRIPTION

LNP STAT-KON ZD000XXR compound is based on Polyphenylene Ether/Polystyrene (PPE/PS) blend which is electrically conductive with improved toughness and reduced carbon sloughing. This is targeted for applications like IC trays and packaging for semi-conductor industry.

| GENERAL INFORMATION   |  |
|-----------------------|--|
| Features              | Electrically Conductive, Low Warpage, Dimensional stability, No PFAS intentionally added |
| Fillers               | Carbon Powder  |
| Polymer Types         | Polyphenylene Ether + PS (PPE+PS)  |
| Processing Techniques | Injection Molding  |

| INDUSTRY   | SUB INDUSTRY      |
|------------|-------------------|
| Industrial | Material Handling |

## TYPICAL PROPERTY VALUES

Revision 20241025

| PROPERTIES                                 | TYPICAL VALUES | UNITS             | TEST METHODS |
|--|----------------|-------------------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>           |                |                   |              |
| Tensile Stress, brk, Type I, 50 mm/min     | 60.3           | MPa               | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min     | 5.2            | %                 | ASTM D638    |
| Tensile Modulus, 50 mm/min                 | 3195           | MPa               | ASTM D638    |
| Flexural Strength, 1.3 mm/min, 50 mm span  | 107            | MPa               | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span   | 3040           | MPa               | ASTM D790    |
| Tensile Stress, break, 50 mm/min           | 59.1           | MPa               | ISO 527      |
| Tensile Strain, break, 50 mm/min           | 4.86           | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min                  | 3077           | MPa               | ISO 527      |
| Flexural Strength, 2 mm/min                | 107            | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min                 | 3245           | MPa               | ISO 178      |
| <b>IMPACT <sup>(1)</sup></b>               |                |                   |              |
| Izod Impact, notched, 23°C                 | 77.5           | J/m               | ASTM D256    |
| Izod Impact, unnotched, 23°C               | 1020           | J/m               | ASTM D4812   |
| Izod Impact, notched 80*10*4 +23°C         | 6.68           | kJ/m <sup>2</sup> | ISO 180/1A   |
| Izod Impact, unnotched 80*10*4 +23°C       | 43.91          | kJ/m <sup>2</sup> | ISO 180/1U   |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm | 6.6            | kJ/m <sup>2</sup> | ISO 179/1eA  |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | 61.4           | kJ/m <sup>2</sup> | ISO 179/1eU  |
| <b>THERMAL <sup>(1)</sup></b>              |                |                   |              |
| HDT, 0.45 MPa, 3.2 mm, unannealed          | 177            | °C                | ASTM D648    |
| HDT, 1.82 MPa, 3.2mm, unannealed           | 165            | °C                | ASTM D648    |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm     | 176            | °C                | ISO 75/Bf    |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm      | 162            | °C                | ISO 75/Af    |
| CTE, -40°C to 40°C, flow                   | 6.4E-5         | 1/°C              | ASTM E831    |
| CTE, -40°C to 40°C, xflow                  | 7.6E-5         | 1/°C              | ASTM E831    |

| PROPERTIES                              | TYPICAL VALUES | UNITS                   | TEST METHODS |
|---|----------------|-------------------------|--------------|
| CTE, -40°C to 40°C, flow                | 6.0E-5         | 1/°C                    | ISO 11359-2  |
| CTE, -40°C to 40°C, xflow               | 7.6E-5         | 1/°C                    | ISO 11359-2  |
| Vicat Softening Temp, Rate A/50         | 193            | °C                      | ASTM D1525   |
| Vicat Softening Temp, Rate B/50         | 182            | °C                      | ISO 306      |
| <b>PHYSICAL <sup>(1)</sup></b>          |                |                         |              |
| Specific Gravity                        | 1.17           | -                       | ASTM D792    |
| Melt Volume Rate, MVR at 300°C/ 10.0 kg | 7.57           | cm <sup>3</sup> /10 min | ISO 1133     |
| Mold Shrinkage, flow <sup>(2)</sup>     | 0.78           | %                       | SABIC method |
| Mold Shrinkage, xflow <sup>(2)</sup>    | 0.74           | %                       | SABIC method |
| <b>ELECTRICAL <sup>(1)</sup></b>        |                |                         |              |
| Surface Resistivity                     | 1.6E+6         | Ω                       | ASTM D257    |
| Volume Resistivity                      | 7.2E+6         | Ω.cm                    | ASTM D257    |
| <b>INJECTION MOLDING <sup>(3)</sup></b> |                |                         |              |
| Drying Temperature                      | 110 – 120      | °C                      |              |
| Drying Time                             | 3 – 5          | Hrs                     |              |
| Melt Temperature                        | 300 – 310      | °C                      |              |
| Nozzle Temperature                      | 300 – 310      | °C                      |              |
| Front - Zone 3 Temperature              | 300 – 310      | °C                      |              |
| Middle - Zone 2 Temperature             | 300 – 310      | °C                      |              |
| Rear - Zone 1 Temperature               | 300 – 310      | °C                      |              |
| Mold Temperature                        | 110 – 130      | °C                      |              |
| Back Pressure                           | 0.1 – 0.3      | MPa                     |              |
| Screw Speed                             | 90 – 110       | rpm                     |              |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.