

# ULTEM™ RESIN HU2300

## DESCRIPTION

ULTEM HU2300 resin is a standard flow 30% glass fiber reinforced polyetherimide resin. The intended use for this material is in medical devices and pharmaceutical applications. The material offers biocompatibility (ISO 10993 or USP Class VI) and Healthcare management of change applies. The material may offer Steam-, Hydrogen Peroxide-, Gamma-, EtO-, UV-C- and E-beam resistance for repeated sterilization cycles. It may offer global food compliance (FDA, CN, EC). The material is RoHS compliant and is intrinsically flame retardant without the use of FR modifiers. It offers UL94 V0 and 5VA ratings. The material can also offer excellent dimension stability, strength, stiffness and creep resistance up to high temperature due to its high glass transition temperature of 217°C. The material is opaque and can be custom colored.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, IR Transparent, Low Moisture Absorption, UV-C resistant, Sustainable (bio-based offerings), Biocompatibility-ISO 10993, Food contact, Healthcare/Formula lock, Non Cl/Br flame retardant, Non halogenated flame retardant, Electroplatable, Autoclave/Steam sterilizable, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, Sterilizable, No PFAS intentionally added, Additive Manufacturing
Fillers	Glass Fiber
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Sheet extrusion, Injection Molding, Profile Extrusion, Extrusion
Regional Availability	Europe, Asia, Americas
INDUSTRY	SUB INDUSTRY
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing

## TYPICAL PROPERTY VALUES

Revision 20230918

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break, 5 mm/min	175	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	10500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	240	MPa	ISO 178
Flexural Modulus, 2 mm/min	9600	MPa	ISO 178
Ball Indentation Hardness, H358/30	165	MPa	ISO 2039-1
Hardness, Rockwell M	110	-	ISO 2039-2
Taber Abrasion, CS-17, 1 kg	20	mg/1000cy	SABIC method
Tensile Stress, brk, Type I, 5 mm/min	175	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
Tensile Modulus, 5 mm/min	10400	MPa	ASTM D638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	230	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	9400	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	250	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9700	MPa	ASTM D790
Hardness, Rockwell M	114	-	ASTM D785

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched 80*10*4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m <sup>2</sup>	ISO 179/1eU
Izod Impact, notched, 23°C	90	J/m	ASTM D256
Izod Impact, notched, -30°C	80	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	470	J/m	ASTM D256
Izod Impact, unnotched, 23°C	600	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	600	J/m	ASTM D4812
<b>THERMAL <sup>(1)</sup></b>			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Af
Vicat Softening Temp, Rate A/50	225	°C	ISO 306
Vicat Softening Temp, Rate B/120	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	213	°C	ISO 306
CTE, -40°C to 150°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 150°C, xflow	4.8E-05	1/°C	ISO 11359-2
Thermal Conductivity	0.31	W/m-°C	ISO 8302
Ball Pressure Test, 125°C +/- 2°C	PASS	-	IEC 60695-10-2
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	212	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	211	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
CTE, -20°C to 150°C, flow	1.8E-05	1/°C	ASTM E831
CTE, -20°C to 150°C, xflow	4.80E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(2)</sup>	180	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	170	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	180	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Density	1.51	g/cm <sup>3</sup>	ISO 1183
Moisture Absorption, (23°C/50% RH/24hrs)	0.1	%	ISO 62-4
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.6	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.16	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.9	%	ISO 62-1
Melt Volume Rate, MVR at 360°C/5.0 kg	6	cm <sup>3</sup> /10 min	ISO 1133
Specific Gravity	1.51	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.16	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.9	%	ASTM D570
Melt Flow Rate, 337°C/6.6 kgf	5	g/10 min	ASTM D1238
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	1E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0016	-	IEC 60250
Dissipation Factor, 1 MHz	0.0025	-	IEC 60250
<b>Dielectric Constant <sup>(3)</sup></b>			
at 1.1 GHz	3.51	-	-
at 5 GHz	3.59	-	-
at 10 GHz	3.60	-	-
<b>Dissipation Factor <sup>(3)</sup></b>			
at 1.1 GHz	0.0029	-	-
at 5 GHz	0.0036	-	-
at 10 GHz	0.0046	-	-
Comparative Tracking Index <sup>(4)</sup>	150	V	IEC 60112
Comparative Tracking Index, M <sup>(4)</sup>	100	V	IEC 60112
Volume Resistivity	3.E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 1.6 mm	24.8	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	30.3	kV/mm	ASTM D149
Relative Permittivity, 1 kHz	3.7	-	ASTM D150
Dissipation Factor, 1 kHz	0.0015	-	ASTM D150
Comparative Tracking Index (UL) {PLC} <sup>(2)</sup>	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1 <sup>(2)</sup>	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3 <sup>(2)</sup>	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3 <sup>(2)</sup>	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4 <sup>(2)</sup>	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC} <sup>(2)</sup>	3	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC} <sup>(2)</sup>	6	PLC Code	ASTM D495
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-221099</a>	-	-
UL Recognized, 94-5VA Flame Class Rating	≥1.2	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.25	mm	UL 94
Glow Wire Ignitability Temperature, 2.0 mm	900	°C	IEC 60695-2-13
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Oxygen Index (LOI)	48	%	ISO 4589
Oxygen Index (LOI)	50	%	ASTM D2863
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	350 – 410	°C	
Nozzle Temperature	345 – 410	°C	
Front - Zone 3 Temperature	345 – 420	°C	
Middle - Zone 2 Temperature	340 – 410	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	135 – 180	°C	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.15 – 0.25	mm	
Screw Speed	40 – 70	rpm	
Screw speed (Circumferential speed)	0.15 – 0.25	m/s	
Back Pressure	0.3 – 1.5	MPa	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Based on SPDR testing technique on dry as molded specimens.
- (4) Value shown here is based on internal measurement.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.