

LNPT[™] THERMOCOMP[™] COMPOUND LF006

LF-1006

REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP LF006 compound is based on Polyetheretherketone (PEEK) resin containing 30% glass fiber.

GENERAL INFORMATION	
Features	High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	176	MPa	ASTM D638
Tensile Strain, break	2	%	ASTM D638
Tensile Modulus, 5 mm/min	13230	MPa	ASTM D638
Flexural Stress	245	MPa	ASTM D790
Flexural modulus	10750	MPa	ASTM D790
Tensile Stress, break	175	MPa	ISO 527
Tensile Strain, break	1.9	%	ISO 527
Tensile Modulus, 1 mm/min	13100	MPa	ISO 527
Flexural Stress	263	MPa	ISO 178
Flexural Modulus	12700	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	875	J/m	ASTM D4812
Izod Impact, notched, 23°C	117	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	13	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	57	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	>298	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	>298	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.62E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	4.68E-05	1/°C	ASTM E831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	1.7E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.84E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	>240	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	>240	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.54	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Density	1.53	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101284444	-	-
UL Recognized, 94V-0 Flame Class Rating	0.78	mm	UL 94
INJECTION MOLDING ⁽³⁾			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.