

NORYL™ RESIN PX2630F

DESCRIPTION

NORYL PX2630F resin is a non-reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This high impact extrusion grade exhibits high impact strength, dimensional stability, hydrolytic stability, and very low moisture absorption. NORYL PX2630F is FDA food contact compliant. *See NORYL PX2630 resin for NON FDA version.

GENERAL INFORMATION	
Features	Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Extrusion
INDUSTRY	SUB INDUSTRY
Industrial	Material Handling
Packaging	Food & Beverage

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	48	MPa	SABIC - Japan Method
Tensile Strain, break	42	%	SABIC - Japan Method
Flexural Stress	76	MPa	ASTM D790
Flexural Modulus	2090	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	330	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Specific Gravity	1.06	-	ASTM D792
Melt Flow Rate, 250°C/10.0 kgf	3.8	g/10 min	ASTM D1238

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.