

LNPT[™] LUBRICOMP[™] COMPOUND WAL34

WAL-4034
REGION ASIA

DESCRIPTION

LNP LUBRICOMP WAL34 compound is based on Polybutylene Terephthalate (PBT) resin containing 15% PTFE, 20% aramid fiber. Added features of this grade include: Internally Lubricated, Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant
Fillers	Aramid Fiber, PTFE
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	57	MPa	ASTM D638
Tensile Strain, break	2.9	%	ASTM D638
Tensile Modulus, 50 mm/min	4500	MPa	ASTM D638
Flexural Stress	103	MPa	ASTM D790
Flexural Modulus	4390	MPa	ASTM D790
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	180	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.42	g/cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽²⁾	1.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	2.2	%	ASTM D955
Dynamic COF	0.24	-	ASTM D3702 Modified: Manual
Static COF	0.21	-	ASTM D3702 Modified: Manual

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.