

LNPTM ELCRINTM WF006NAiQ

ER009840

DESCRIPTION

LNP ELCRIN WF006NAiQ is an iQ PBT based compound containing 30% glass for NMT application. Added features of this material include: >25% PCR, high metal bonding strength, and good chemical resistance.

GENERAL INFORMATION	
Features	Chemical Resistance, High Flow, Sustainable (Advanced Recycling), Nano molding technology, Dimensional stability, High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260826

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	113	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.7	%	ASTM D638
Tensile Modulus, 5 mm/min	8800	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	178	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7770	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	111	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	8700	MPa	ISO 527
Flexural Strength, 2 mm/min	173	MPa	ISO 178
Flexural Modulus, 2 mm/min	7400	MPa	ISO 178
Bonding Strength ("T" treatment, shear type)	32	MPa	ISO 19095
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	910	J/m	ASTM D4812
Izod Impact, notched, 23°C	150	J/m	ASTM D256
Izod Impact, notched, -30°C	110	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	51	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14.5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	56	kJ/m ²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	15	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	150	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	151	°C	ISO 306
HDT, 1.82 MPa, 3.2mm, unannealed	172	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	206	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	201	°C	ISO 75/Bf
CTE, -40°C to 40°C, flow	2.4E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	2.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.6E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	75	°C	UL 746B
PHYSICAL ⁽¹⁾			
Moisture Absorption, (23°C/50% RH/24hrs)	0.02	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.04	%	ISO 62-1
Density	1.48	g/cm ³	ISO 1183
Melt Flow Rate			
250°C/5.0 kgf	12	g/10 min	ASTM D1238
275°C/5 kgf	24	g/10 min	ASTM D1238
Melt Volume Rate			
250°C/5.0 kg	9	cm ³ /10 min	ISO 1133
275°C/5 kg	19	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow ⁽³⁾	0.2 – 0.3	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.4 – 0.5	%	SABIC method
ELECTRICAL ⁽¹⁾			
Dielectric Constant			
1.1 GHz	3.65	-	SABIC method
1.9 GHz	3.69	-	SABIC method
5 GHz	3.66	-	SABIC method
10 GHz	3.64	-	SABIC method
Dissipation Factor			
1.1 GHz	0.015	-	SABIC method
1.9 GHz	0.014	-	SABIC method
5 GHz	0.013	-	SABIC method
10 GHz	0.011	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-104509729	-	-
UL Recognized, 94HB Flame Class Rating	≥0.7	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature ⁽⁵⁾	100 – 160	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.
- (5) Suggest to use narrow mold temperature 140C~160C for NMT application.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.