

LNPT[™] LUBRICOMP[™] COMPOUND MX06404

MFL-4034 HS LE

REGION ASIA

DESCRIPTION

LNP LUBRICOMP MX06404 compound is based on Polypropylene (PP) resin containing 20% glass fiber and 15% PTFE. Added features of this grade include: Heat Stabilized, Low Extractable, Wear Resistant.

GENERAL INFORMATION	
Features	Heat Stabilized, Wear resistant, Food contact
Fillers	Glass Fiber, PTFE
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	35	MPa	ASTM D638
Tensile Strain, break	1	%	ASTM D638
Tensile Modulus, 50 mm/min	5810	MPa	ASTM D638
Flexural Stress	55	MPa	ASTM D790
Flexural Modulus	4820	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	150	J/m	ASTM D4812
Izod Impact, notched, 23°C	40	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	103	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.14	g/cm ³	ASTM D792

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.