

LNPTTM LUBRICOMPTM COMPOUND DFP36

DFL-4536

REGION AMERICAS

DESCRIPTION

LNP LUBRICOMP DFP36 compound is based on Polycarbonate (PC) resin containing 30% glass fiber, 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE/Silicone
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	8700	MPa	ISO 527
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	736	J/m	ASTM D4812
Izod Impact, notched, 23°C	179	J/m	ASTM D256
Multiaxial Impact	7	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	49	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	146	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Moisture Absorption, (23°C/50% RH/24 hrs)	0.08	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.1 – 0.3	%	ASTM D955
Moisture Absorption (23°C / 50% RH)	0.12	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.