

# NORYL PPX™ RESIN PPX630F

REGION AMERICAS

## DESCRIPTION

NORYL PPX630F resin is a 30% glass fiber reinforced alloy of polyphenylene ether (PPE) + polypropylene (PP). This injection moldable grade is NSF 61 certified and exhibits high elongation and stiffness along with temperature performance, impact resistance, hydrolytic and dimensional stability. NORYL PPX630F resin is an excellent candidate for copper and brass replacement in water management applications such as boiler manifolds, condensers, and hydro blocks.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Food contact, Potable water safe, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PP (PPE+PP)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Water Management

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 5 mm/min	79	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	79	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	7.7	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	129	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5550	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	827	J/m	ASTM D4812
Izod Impact, notched, 23°C	165	J/m	ASTM D256
Izod Impact, notched, -30°C	101	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	19	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	20	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
Vicat Softening Temp, Rate B/50	162	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	155	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	133	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.44E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.74E-05	1/°C	ASTM E831
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.2 – 0.23	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, xflow, 3.2 mm <sup>(2)</sup>	0.25 – 0.76	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	2.6	g/10 min	ASTM D1238
<b>FLAME CHARACTERISTICS <sup>(3)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-221227</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	65 – 75	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 300	°C	
Nozzle Temperature	260 – 300	°C	
Front - Zone 3 Temperature	255 – 295	°C	
Middle - Zone 2 Temperature	250 – 290	°C	
Rear - Zone 1 Temperature	245 – 290	°C	
Mold Temperature	40 – 65	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.051 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.