LNP™ COLORCOMP™ COMPOUND A1000H

DESCRIPTION

LNP COLORCOMP A1000H compound is based on unfilled Acrylonitrile Butadiene Styrene (ABS) resin. Added features of this grade include: Healthcare

GENERAL INFORMATION	
Features	Aesthetics/Visual effects, Healthcare/Formula lock, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding
Regional Availability	Europe, Asia, Americas

INDUSTRY	SUB INDUSTRY
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20260327

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 5 mm/min	44	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	33	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	24	%	ASTM D638
Tensile Modulus, 5 mm/min	2270	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	72	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	50	MPa	ISO 527
Tensile Stress, break, 5 mm/min	35	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.6	%	ISO 527
Tensile Strain, break, 5 mm/min	24.8	%	ISO 527
Tensile Modulus, 1 mm/min	2530	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	76	MPa	ISO 178
Flexural Modulus, 2 mm/min	2410	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	320	J/m	ASTM D256
Izod Impact, notched, -30°C	133	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	30	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	23	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	18	kJ/m²	ISO 179/1eA
THERMAL [1]			
Vicat Softening Temp, Rate B/50	98	°C	ASTM D1525

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D648
CTE, -40°C to 40°C, flow	8.82E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.82E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	8.82E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.82E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	100	°C	ISO 306
Vicat Softening Temp, Rate B/120	100	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	80	°C	ISO 75/Af
PHYSICAL [1]			
Specific Gravity	1.05	-	ASTM D792
Melt Flow Rate			
230°C/3.8 kg	5.6	g/10 min	ASTM D1238
220°C/10.0 kg	19	g/10 min	ISO 1133
Melt Viscosity, 240°C, 1000 sec-1	2300	Poise	ASTM D3825
Density	1.05	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	1	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate			
220°C/5.0 kg	14	cm³/10 min	ISO 1133
INJECTION MOLDING [2]			
Drying Temperature	80 – 95	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.05 – 0.1	%	
Melt Temperature	220 – 260	°C	
Nozzle Temperature	220 – 260	°C	
Front - Zone 3 Temperature	215 – 240	°C	
Middle - Zone 2 Temperature	205 – 225	°C	
Rear - Zone 1 Temperature	190 – 210	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved