

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND FF004

## DESCRIPTION

LNP THERMOCOMP FF004 is a compound based on Polyethylene (PE) resin containing 20% Glass Fiber.

GENERAL INFORMATION	
Features	High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyethylene, Unspecified (PE, Unspecified)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Consumer	Consumer Goods, Sport/Leisure
Hygiene and Healthcare	General Healthcare
Industrial	Industrial General

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break	40	MPa	ASTM D638
Tensile Stress, yld, Type I, 5 mm/min	40	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	35	MPa	ASTM D638
Tensile Strain, break	4.3	%	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4.6	%	ASTM D638
Tensile Modulus, 50 mm/min	4210	MPa	ASTM D638
Flexural Stress	48	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	54	MPa	ASTM D790
Flexural Modulus	2410	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2980	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	37	MPa	ISO 527
Tensile Stress, break, 5 mm/min	31	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.5	%	ISO 527
Tensile Strain, break, 5 mm/min	4.2	%	ISO 527
Tensile Modulus, 1 mm/min	3420	MPa	ISO 527
Flexural Stress	51	MPa	ISO 178
Flexural Modulus, 2 mm/min	2840	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	337	J/m	ASTM D4812
Izod Impact, notched, 23°C	65	J/m	ASTM D256
Multiaxial Impact	3	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	10	J	ASTM D3763

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 +23°C	17	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	126	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	102	°C	ASTM D648
CTE, -30°C to 30°C, flow	5.6E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	1.23E-04	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	92	°C	ISO 75/Af
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.09	-	ASTM D792
Density	1.08	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.02	%	ASTM D570
Moisture Absorption (23°C / 50% RH)	0.01	%	ISO 62
<b>INJECTION MOLDING <sup>(2)</sup></b>			
Drying Temperature	80	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	230	°C	
Front - Zone 3 Temperature	220 – 230	°C	
Middle - Zone 2 Temperature	210 – 220	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	40 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.