

# NORYL PPX™ RESIN PPX640

REGION ASIA

## DESCRIPTION

NORYL PPX640 resin is a 40% glass fiber reinforced alloy of polyphenylene ether (PPE) + Polypropylene (PP). This injection moldable grade exhibits high stiffness along with temperature performance, impact resistance, hydrolytic stability, and dimensional stability. NORYL PPX640 resin is an excellent candidate for applications requiring a good chemical resistance and high stiffness.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PP (PPE+PP)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck
Building and Construction	Water Management
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 5 mm/min	95	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	95	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	6.4	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	150	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	8310	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	576	J/m	ASTM D4812
Izod Impact, notched, 23°C	106	J/m	ASTM D256
Izod Impact, notched, -30°C	96	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	16	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	14	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
Vicat Softening Temp, Rate B/50	163	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	158	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	146	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.08E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E831
<b>PHYSICAL <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Gravity	1.3	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.17 – 0.18	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm <sup>(2)</sup>	0.27 – 0.61	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	1.3	g/10 min	ASTM D1238
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	65 – 75	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 305	°C	
Nozzle Temperature	260 – 305	°C	
Front - Zone 3 Temperature	255 – 300	°C	
Middle - Zone 2 Temperature	250 – 290	°C	
Rear - Zone 1 Temperature	245 – 290	°C	
Mold Temperature	40 – 65	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.051 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.