

LNPTM COLORCOMPTM COMPOUND D1000RFJ

DESCRIPTION

LNP COLORCOMP D1000RFJ compound is based on unfilled Polycarbonate (PC) resin. Added features of this grade include: Healthcare, Low Extractable, Mold Release and UL Rated HB.

This material is food contact compliant in most jurisdictions – exceptions may exist, request a declaration for details.

| GENERAL INFORMATION | |
|-----------------------|---|
| Features | High Flow, Aesthetics/Visual effects, Food contact, Healthcare/Formula lock, Enhanced mold release, No PFAS intentionally added |
| Fillers | Unreinforced |
| Polymer Types | Polycarbonate (PC) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|---------------------------|---|
| Building and Construction | Water Management |
| Consumer | Home Appliances |
| Hygiene and Healthcare | Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing |
| Packaging | Industrial Packaging, Food & Beverage |

TYPICAL PROPERTY VALUES

Revision 20250404

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 62 | MPa | ASTM D638 |
| Tensile Stress, brk, Type I, 50 mm/min | 68 | MPa | ASTM D638 |
| Tensile Strain, yld, Type I, 50 mm/min | 7 | % | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 125 | % | ASTM D638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 96 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2340 | MPa | ASTM D790 |
| Hardness, Rockwell M | 70 | - | ASTM D785 |
| Hardness, Rockwell R | 118 | - | ASTM D785 |
| Taber Abrasion, CS-17, 1 kg | 10 | mg/1000cy | ASTM D1044 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, unnotched, 23°C | 3204 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 694 | J/m | ASTM D256 |
| Tensile Impact Strength, Type S | 546 | kJ/m ² | ASTM D1822 |
| Falling Dart Impact (D 3029), 23°C | 169 | J | ASTM D3029 |
| Instrumented Dart Impact Energy @ peak, 23°C | 62 | J | ASTM D3763 |
| Izod Impact, unnotched 80*10*3 +23°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*3 -30°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*3 +23°C | 12 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*3 -30°C | 10 | kJ/m ² | ISO 180/1A |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|-----------------------------------|--------------------|--------------|
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| THERMAL ⁽¹⁾ | | | |
| Vicat Softening Temp, Rate B/50 | 154 | °C | ASTM D1525 |
| HDT, 0.45 MPa, 6.4 mm, unannealed | 137 | °C | ASTM D648 |
| HDT, 1.82 MPa, 6.4 mm, unannealed | 129 | °C | ASTM D648 |
| CTE, -40°C to 95°C, flow | 6.84E-05 | 1/°C | ASTM E831 |
| Specific Heat | 1.25 | J/g.°C | ASTM C351 |
| Thermal Conductivity | 0.19 | W/m.°C | ASTM C177 |
| Relative Temp Index, Elec ⁽²⁾ | 130 | °C | UL 746B |
| Relative Temp Index, Mech w/impact ⁽²⁾ | 130 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact ⁽²⁾ | 130 | °C | UL 746B |
| PHYSICAL ⁽¹⁾ | | | |
| Specific Gravity | 1.2 | - | ASTM D792 |
| Specific Volume | 0.83 | cm ³ /g | ASTM D792 |
| Density | 1.19 | g/cm ³ | ASTM D792 |
| Water Absorption, (23°C/24hrs) | 0.15 | % | ASTM D570 |
| Water Absorption, (23°C/Saturated) | 0.35 | % | ASTM D570 |
| Water Absorption, equilibrium, 100°C | 0.58 | % | ASTM D570 |
| Mold Shrinkage, flow, 3.2 mm ⁽³⁾ | 0.5 – 0.7 | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 16 | g/10 min | ASTM D1238 |
| OPTICAL ⁽¹⁾ | | | |
| Light Transmission, 2.54 mm | 88 | % | ASTM D1003 |
| Haze, 2.54 mm | 1 | % | ASTM D1003 |
| Refractive Index | 1.586 | - | ASTM D542 |
| ELECTRICAL ^{(1) (2)} | | | |
| Volume Resistivity | >1.E+17 | Ω.cm | ASTM D257 |
| Dielectric Strength, in air, 3.2 mm | 14.9 | kV/mm | ASTM D149 |
| Relative Permittivity, 50/60 Hz | 3.17 | - | ASTM D150 |
| Relative Permittivity, 1 MHz | 2.96 | - | ASTM D150 |
| Dissipation Factor, 50/60 Hz | 0.0009 | - | ASTM D150 |
| Dissipation Factor, 1 MHz | 0.01 | - | ASTM D150 |
| Comparative Tracking Index (UL) {PLC} | 2 | PLC Code | UL 746A |
| Hot-Wire Ignition (HWI), PLC 3 | ≥1.1 | mm | UL 746A |
| Hot-Wire Ignition (HWI), PLC 2 | ≥1.5 | mm | UL 746A |
| High Amp Arc Ignition (HAI), PLC 2 | ≥1.1 | mm | UL 746A |
| High Amp Arc Ignition (HAI), PLC 1 | ≥1.5 | mm | UL 746A |
| High Voltage Arc Track Rate {PLC} | 2 | PLC Code | UL 746A |
| FLAME CHARACTERISTICS ⁽²⁾ | | | |
| UL Yellow Card Link | E121562-104419595 | - | - |
| UL Recognized, 94HB Flame Class Rating | ≥0.7 | mm | UL 94 |
| INJECTION MOLDING ⁽⁴⁾ | | | |
| Drying Temperature | 120 | °C | |
| Drying Time | 3 – 4 | Hrs | |
| Drying Time (Cumulative) | 48 | Hrs | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 280 – 305 | °C | |
| Nozzle Temperature | 275 – 300 | °C | |
| Front - Zone 3 Temperature | 280 – 305 | °C | |
| Middle - Zone 2 Temperature | 270 – 295 | °C | |
| Rear - Zone 1 Temperature | 260 – 280 | °C | |
| Mold Temperature | 70 – 95 | °C | |
| Back Pressure | 0.3 – 0.7 | MPa | |
| Screw Speed | 40 – 70 | rpm | |
| Shot to Cylinder Size | 40 – 60 | % | |
| Vent Depth | 0.025 – 0.076 | mm | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.