

ELCRES™ HTV150A FILM

PRODUCT DATASHEET

KEY FEATURES & BENEFITS

SABIC's ELCRES HTV150A dielectric film offers high temperature solutions for professional grade DC-Link power capacitors, addressing future high voltage industry requirements. ELCRES™ HTV150A dielectric film exhibits stable performance at -40°C to +150°C and frequency up to 100 kHz, including stable capacitance, good insulation resistance, stable dielectric constant (Dk) and low dissipation factor (Df). SABIC's HTV150A dielectric film has been validated by customers with both film-foil and metallized electrodes, including flat aluminum, heavy edge/light body and fused/patterned electrode designs. ELCRES HTV150A dielectric film can be processed on existing metallization, slitting, capacitor winding and squashing/flattening equipment. Capacitors made with HTV150A films meet damp heat aging requirements (85°C & 85%RH for 1000 hours) with little or no change in dielectric performance.



TYPICAL PROPERTIES*

	Test method	Unit	Value (5µm)	Value (3µm)
Thickness				
Mean Thickness	In-line x-ray	µm	5.0	3.0
Thickness variation	In-line x-ray	% (3σ / average thickness)	2.1	4.3
Electrical				
Breakdown Strength (BDS) 23°C	ASTM D149	V/µm	765	
Breakdown Strength (BDS) 150°C	ASTM D149	V/µm	725	
Dielectric Constant (Dk) at 27°C, 1 kHz (metallized film)	ASTM D150		2.9	
Dissipation Factor (Df) at 27°C, 1 kHz (metallized film)	ASTM D150		0.0017	
Clearing Counts @ 200 V/µm	Bosch Test	Counts/m ²	1.5	--
Clearing Counts @ 250 V/µm	Bosch Test	Counts/m ²	2.5	--
Clearing Counts @ 300 V/µm	Bosch Test	Counts/m ²	5.5	--
Thermal				
Coefficient of Thermal Expansion (MD)	JIS K7197	(x10 ⁻⁶ /°C)	101	103
Coefficient of Thermal Expansion (TD)	JIS K7197	(x10 ⁻⁶ /°C)	138	149
Glass Transition Temperature (Tg)	ASTM D3418	°C	206	206
Shrinkage @ 150°C / 0.5 hr (MD)	JIS K7133	%	-0.21	-0.37
Shrinkage @ 150°C / 0.5 hr (TD)	JIS K7133	%	-0.21	-0.23
Shrinkage @ 170°C / 0.5 hr (MD)	JIS K7133	%	-0.34	-0.50
Shrinkage @ 170°C / 0.5 hr (TD)	JIS K7133	%	-0.25	-0.24

	Test method	Unit	Value (5µm)	Value (3µm)
Physical				
Density	ASTM D792	g/cm ³	1.12	1.12
Water Absorption, Equilibrium, 23°C, 24 hours	ASTM D570	%	0.30	0.30
Surface roughness of roll face	JIS B0601	µm	0.23	0.21
Surface roughness of air face	JIS B0601	µm	0.25	0.23
COF (Dynamic) - Metal/Bare film	JIS K7125		0.44	0.51
COF (Static) - Metal/Bare film	JIS K7125		0.47	0.56
Mechanical				
Tensile Modulus (MD)	JIS K6781	MPa	2510	2490
Tensile Strength @ Break (MD)	JIS K6781	MPa	66	65
Tensile Elongation to Break (MD)	JIS K6781	%	39	22
Tensile Modulus (TD)	JIS K6781	MPa	2440	2410
Tensile Strength @ Break (TD)	JIS K6781	MPa	64	60
Tensile Elongation @ Break (TD)	JIS K6781	%	17	11
Tear Strength (MD)	JIS K7128	N/mm	100	83

* These are typical properties and are not intended for specification purposes. Reported values are based on 5 & 3 µm film thickness and are tested at machine direction unless otherwise noted. BDS, Dk and Df are based on 3 µm film thickness.

MANUFACTURING SPECIFICATIONS

Gauge	5 µm & 3 µm
Standard Roll Width	620 mm
Standard Roll Length	5000 m
Color code	1000
Color	Natural clear

CONTACT INFORMATION

SABIC SPECIALTIES BUSINESS

AMERICAS

E: Specialties.Americas@sabic-hpp.com
T: +1 800 845 0600

ASIA PACIFIC

E: Specialties.Asia@sabic-hpp.com
T: +86 400 833 1033

EUROPE

E: Specialties.EMEA@sabic-hpp.com
T: +36 1 288 3040



SABIC MATERIAL FINDER

Find the right Specialties material for your application ▶





MOBILITY

DISCLAIMER: ANY SALE BY SABIC, ITS SUBSIDIARIES AND AFFILIATES (EACH A “SELLER”), IS MADE EXCLUSIVELY UNDER SELLER’S STANDARD CONDITIONS OF SALE (AVAILABLE UPON REQUEST) UNLESS AGREED OTHERWISE IN WRITING AND SIGNED ON BEHALF OF THE SELLER. WHILE THE INFORMATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2024 Saudi Basic Industries Corporation (SABIC). All Rights Reserved. Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.