LNP™ THERMOCOMP™ Compound WFC06IXP

DESCRIPTION

LNP THERMOCOMP COMPOUND WFC06IXP is a compound based on Polybutylene terephthalate (PBT) containing Glass Fiber. Added features of this material include Chemical Resistance, Enhanced Dimensional Stability, Low Warpage, Dielectrics.

GENERAL INFORMATION	
Features	Chemical Resistance, Low Warpage, Dielectrics, Dimensional stability, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Interiors
Consumer	Home Appliances, Commercial Appliance
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260319

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	8370	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	190	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7660	MPa	ASTM D790
IMPACT [1]			
Izod Impact, notched, -20°C	120	J/m	ASTM D256
Izod Impact, notched, 23°C	160	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1100	J/m	ASTM D4812
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	15	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	65	kJ/m²	ISO 179/1eU
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	218	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	193	°C	ASTM D648
CTE			
23°C to 80°C, flow	3.0E-05	1/°C	ASTM E831
23°C to 80°C, xflow	8.0E-05	1/°C	ASTM E831
PHYSICAL [1]			
Specific Gravity	1.5	-	ASTM D792
Melt Volume Rate, MVR at 260°C/5.0 kg	11	cm³/10 min	ISO 1133
Mold Shrinkage, flow [2]	0.2 – 0.4	%	SABIC method
Mold Shrinkage, xflow [2]	0.4 – 0.6	%	SABIC method

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL [1]			
Dielectric Constant			
1.1 GHz	3.5	-	SABIC method
1.9 GHz	3.7	-	SABIC method
5 GHz	3.6	-	SABIC method
10 GHz	3.6	-	SABIC method
20 GHz	3.4	-	SABIC method
77 GHz	3.5	-	SABIC method
Dissipation Factor			
1.1 GHz	0.008	-	SABIC method
1.9 GHz	0.008	-	SABIC method
5 GHz	0.007	-	SABIC method
10 GHz	0.007	-	SABIC method
20 GHz	0.008	-	SABIC method
77 GHz	0.009	-	SABIC method
FLAME CHARACTERISTICS [3]			
UL Yellow Card Link	E207780-104566020	-	-
UL Recognized, 94HB Flame Class Rating	≥1.0	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Melt Temperature	260 – 290	°C	
Nozzle Temperature	265 – 295	°C	
Front - Zone 3 Temperature	260 – 290	°C	
Middle - Zone 2 Temperature	260 – 290	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	50 – 110	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved