

# LNPT<sup>™</sup> ELCRIN<sup>™</sup> EXL9414B

## DESCRIPTION

ELCRIN EXL9414B polycarbonate (PC) siloxane copolymer resin is a medium flow, non-chlorinated, non-brominated flame retardant opaque injection molding (IM) grade with major component synthesized from Bio source. This resin offers low temperature ductility (-30°C), thin wall flame retardant capability (UL94 V0 @ 1.0mm), and in combination with excellent processability and release with opportunities for shorter IM cycle times compared to standard. PC. ELCRIN EXL9414B copolymer resin is a product available in wide range of opaque colors and may be an excellent candidate for a wide variety of applications.

| GENERAL INFORMATION   |   |
|-----------------------|---|
| Features              | Flame Retardant, Good Processability, Non Cl/Br flame retardant, Low temperature impact |
| Fillers               | Unreinforced  |
| Brands                | LNPT <sup>™</sup> ELCRIN <sup>™</sup>   |
| Polymer Types         | Polycarbonate (PC)  |
| Processing Techniques | Injection Molding   |

| INDUSTRY                   | SUB INDUSTRY                        |
|----------------------------|-------------------------------------|
| Consumer                   | Personal Accessory, Home Appliances |
| Electrical and Electronics | Mobile Phone - Computer - Tablets   |
| Industrial                 | Electrical                          |

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES                                | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>          |                |       |              |
| Tensile Stress, yld, Type I, 50 mm/min    | 56             | MPa   | ASTM D638    |
| Tensile Stress, brk, Type I, 50 mm/min    | 62             | MPa   | ASTM D638    |
| Tensile Strain, yld, Type I, 50 mm/min    | 5.8            | %     | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min    | 107            | %     | ASTM D638    |
| Tensile Modulus, 50 mm/min                | 2110           | MPa   | ASTM D638    |
| Flexural Strength, 1.3 mm/min, 50 mm span | 88             | MPa   | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span  | 2190           | MPa   | ASTM D790    |
| Tensile Stress, yield, 50 mm/min          | 57             | MPa   | ISO 527      |
| Tensile Stress, break, 50 mm/min          | 60             | MPa   | ISO 527      |
| Tensile Strain, yield, 50 mm/min          | 5.6            | %     | ISO 527      |
| Tensile Strain, break, 50 mm/min          | 106            | %     | ISO 527      |
| Tensile Modulus, 1 mm/min                 | 2140           | MPa   | ISO 527      |
| Flexural Strength, 2 mm/min               | 86             | MPa   | ISO 178      |
| Flexural Modulus, 2 mm/min                | 2180           | MPa   | ISO 178      |
| Hardness, Rockwell R                      | 117            | -     | ASTM D785    |
| Hardness, Rockwell L                      | 83             | -     | ASTM D785    |
| <b>IMPACT <sup>(1)</sup></b>              |                |       |              |
| Izod Impact, notched, 23°C                | 880            | J/m   | ASTM D256    |
| Izod Impact, notched, -30°C               | 660            | J/m   | ASTM D256    |

| PROPERTIES   | TYPICAL VALUES   | UNITS                   | TEST METHODS   |
|--|--|-------------------------|----------------|
| Izod Impact, notched 80*10*3 +23°C                           | 69   | kJ/m <sup>2</sup>       | ISO 180/1A     |
| Izod Impact, notched 80*10*3 -30°C                           | 46   | kJ/m <sup>2</sup>       | ISO 180/1A     |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm                   | 75   | kJ/m <sup>2</sup>       | ISO 179/1eA    |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm                  | 29   | kJ/m <sup>2</sup>       | ISO 179/1eA    |
| Instrumented Dart Impact Total Energy, 23°C                  | 67   | J                       | ASTM D3763     |
| <b>THERMAL <sup>(1)</sup></b>                                |  |                         |                |
| HDT, 0.45 MPa, 3.2 mm, unannealed                            | 134  | °C                      | ASTM D648      |
| HDT, 1.82 MPa, 3.2mm, unannealed                             | 118  | °C                      | ASTM D648      |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm                      | 131  | °C                      | ISO 75/Be      |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm                      | 117  | °C                      | ISO 75/Ae      |
| CTE, -40°C to 40°C, flow                                     | 6.91E-05   | 1/°C                    | ASTM E831      |
| CTE, -40°C to 40°C, xflow                                    | 7.27E-05   | 1/°C                    | ASTM E831      |
| CTE, 23°C to 80°C, flow                                      | 7.42E-05   | 1/°C                    | ISO 11359-2    |
| CTE, 23°C to 80°C, xflow                                     | 7.64E-05   | 1/°C                    | ISO 11359-2    |
| Vicat Softening Temp, Rate B/50                              | 136  | °C                      | ISO 306        |
| Vicat Softening Temp, Rate B/120                             | 138  | °C                      | ISO 306        |
| Relative Temp Index, Elec <sup>(2)</sup>                     | 80   | °C                      | UL 746B        |
| Relative Temp Index, Mech w/impact <sup>(2)</sup>            | 80   | °C                      | UL 746B        |
| Relative Temp Index, Mech w/o impact <sup>(2)</sup>          | 80   | °C                      | UL 746B        |
| <b>PHYSICAL <sup>(1)</sup></b>                               |  |                         |                |
| Specific Gravity   | 1.19   | -                       | ASTM D792      |
| Density  | 1.19   | g/cm <sup>3</sup>       | ISO 1183       |
| Melt Flow Rate, 300°C/1.2 kgf                                | 11.5   | g/10 min                | ASTM D1238     |
| Melt Volume Rate, MVR at 300°C/1.2 kg                        | 10   | cm <sup>3</sup> /10 min | ISO 1133       |
| Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>                  | 0.4 – 0.8  | %                       | SABIC method   |
| Mold Shrinkage, xflow, 3.2 mm <sup>(3)</sup>                 | 0.4 – 0.8  | %                       | SABIC method   |
| <b>ELECTRICAL <sup>(1)</sup></b>                             |  |                         |                |
| Surface Resistivity  | >1.E+16  | Ω                       | ASTM D257      |
| Volume Resistivity   | >1.E+16  | Ω.cm                    | ASTM D257      |
| Dielectric Constant (Dk), 1.1 GHz                            | 2.78   | -                       | ASTM ES 7-83   |
| Dissipation Factor (Df), 1.1 GHz                             | 0.006  | -                       | ASTM ES 7-83   |
| Dielectric Strength, in oil, 3.2 mm                          | 13   | kV/mm                   | ASTM D149      |
| <b>FLAME CHARACTERISTICS <sup>(2)</sup></b>                  |  |                         |                |
| UL Yellow Card Link  | <a href="https://www.ul.com/Products/Plastics/Engineering-Plastics/UL-94-Flame-Rated-Plastics">E207780-102896543</a> | -                       | -              |
| UL Recognized, 94-5VA Flame Class Rating                     | ≥3.1   | mm                      | UL 94          |
| UL Recognized, 94-5VB Flame Class Rating                     | ≥1.5   | mm                      | UL 94          |
| UL Recognized, 94V-0 Flame Class Rating                      | ≥1.0   | mm                      | UL 94          |
| UL Recognized, 94V-1 Flame Class Rating                      | ≥0.8   | mm                      | UL 94          |
| UL Recognized, 94V-2 Flame Class Rating                      | ≥0.50  | mm                      | UL 94          |
| Glow Wire Flammability Index 960°C, passes at <sup>(1)</sup> | 1  | mm                      | IEC 60695-2-12 |
| Oxygen Index (LOI) <sup>(1)</sup>                            | 39   | %                       | ISO 4589       |
| <b>INJECTION MOLDING <sup>(4)</sup></b>                      |  |                         |                |
| Drying Temperature   | 120  | °C                      |                |
| Drying Time  | 3 – 4  | Hrs                     |                |
| Drying Time (Cumulative)                                     | 48   | Hrs                     |                |

| PROPERTIES                  | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Maximum Moisture Content    | 0.02           | %     |              |
| Melt Temperature            | 295 – 315      | °C    |              |
| Nozzle Temperature          | 290 – 310      | °C    |              |
| Front - Zone 3 Temperature  | 295 – 315      | °C    |              |
| Middle - Zone 2 Temperature | 280 – 305      | °C    |              |
| Rear - Zone 1 Temperature   | 270 – 295      | °C    |              |
| Mold Temperature            | 70 – 95        | °C    |              |
| Back Pressure               | 0.3 – 0.7      | MPa   |              |
| Screw Speed                 | 40 – 70        | rpm   |              |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.