

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND LF008EX1

## DESCRIPTION

LNP THERMOCOMP LF008EX1 compound is based on Polyetheretherketone (PEEK) resin containing 40% glass fiber. Added features of this grade include: High Modulus and Strength, Easy Molding and Low Warpage.

GENERAL INFORMATION	
Features	Good Processability, Low Warpage, High stiffness/Strength, High temperature resistance
Fillers	Glass Fiber
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

## TYPICAL PROPERTY VALUES

Revision 20231204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Flexural Strength, 1.3 mm/min, 50 mm span	260	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	12300	MPa	ASTM D790
Tensile Stress, brk, Type I, 5 mm/min	190	MPa	ASTM D638
Tensile Modulus, 5 mm/min	14000	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.2	%	ASTM D638
Flexural Strength, 2 mm/min	265	MPa	ISO 178
Flexural Modulus, 2 mm/min	12700	MPa	ISO 178
Tensile Stress, break, 5 mm/min	193	MPa	ISO 527
Tensile Modulus, 1 mm/min	13800	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	134	J/m	ASTM D256
Izod Impact, unnotched, 23°C	873	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	58	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	60	kJ/m <sup>2</sup>	ISO 179/1eU
Multiaxial Impact	20	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	315	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	337	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	310	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	336	°C	ISO 75/Bf
CTE, -40°C to 120°C, flow	1.9E-05	1/°C	ASTM E831
CTE, -40°C to 120°C, xflow	3.7E-05	1/°C	ASTM E831
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.62	-	ASTM D792
Mold Shrinkage, flow, 24 hrs <sup>(2)</sup>	0.2 – 0.3	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(2)</sup>	0.4 – 0.5	%	ASTM D955
Density	1.61	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
<b>ELECTRICAL <sup>(1)</sup></b>			
Dielectric Constant, 1.1 GHz	4.02	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0042	-	SABIC method
Dielectric Constant, 1.9 GHz	4.03	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0045	-	SABIC method
<b>FLAME CHARACTERISTICS</b>			
UL Yellow Card Link <sup>(3)</sup>	<a href="#">E121562-647646</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	3.0	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	120 – 150	°C	
Drying Time	3 – 5	Hrs	
Nozzle Temperature	380 – 400	°C	
Melt Temperature	380 – 400	°C	
Front - Zone 3 Temperature	370 – 380	°C	
Middle - Zone 2 Temperature	360 – 370	°C	
Rear - Zone 1 Temperature	290 – 300	°C	
Mold Temperature	170 – 200	°C	
Screw Speed	50 – 100	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.