

DIANHYDRIDES & IMIDES

1040A

REGION AMERICAS

DESCRIPTION

Transparent, high flow polyetherimide.

TYPICAL PROPERTY VALUES

Revision 20180330

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	97	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D 638
Tensile Modulus, 5 mm/min	3440	MPa	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	159	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	3510	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	470	J/m	ASTM D 4812
Izod Impact, notched, 23°C	21	J/m	ASTM D 256
Gardner, 23°C	8	J	ASTM D 3029
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	196	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.27	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	6.6	g/10 min	ASTM D 1238

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.