

ULTEM™ RESIN 2312

REGION ASIA

DESCRIPTION

30% Milled glass filled, enhanced flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial	Electrical, Material Handling, Textile, Eyewear
Mass Transportation	Rail
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20230725

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	103	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.5	%	ASTM D638
Tensile Modulus, 5 mm/min	5990	MPa	ASTM D638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	179	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	6550	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	309	J/m	ASTM D256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	207	°C	ASTM D648
CTE, -40°C to 150°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 150°C, xflow	2.7E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec ⁽¹⁾	170	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	170	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	170	°C	UL 746B
PHYSICAL			
Specific Gravity	1.51	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.18	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.98	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.3 – 0.4	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.45 – 0.55	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	10.1	g/10 min	ASTM D1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL			
Relative Permittivity, 1 kHz	3.7	-	ASTM D150
Relative Permittivity, 1 MHz	3.49	-	ASTM D150
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥0.81	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥3	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥0.81	mm	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D495
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E121562-221100	-	-
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.5 mm	875	°C	IEC 60695-2-13
UL Recognized, 94V-0 Flame Class Rating	≥0.81	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™